

NORMAL WEAR NORMAL CONTAMINATION FLUID CONDITION NORMAL



Store 9 - Marietta JOHN DEERE 250G 1FF250GXCNF612054 Component Hydraulic System

HITACHI HYDRAULIC SUPER EX 46HN (63 GAL)

RECOMMENDATION	Test	UOM	Method
Posample at the payt capilog interval to monitor	Sample Number		Client Info
Resample at the next service interval to monitor.	Sample Date		Client Info
	Machine Age	hrs	Client Info
	Oil Age	hrs	Client Info
	Filter Age	hrs	Client Info
	Oil Changed		Client Info
	Filter Changed		Client Info
	Sample Status		
WEAR	PQ		ASTM D818
	Iron	ppm	ASTM D5185r
All component wear rates are normal.	Chromium	ppm	ASTM D5185r
	Nickel	ppm	ASTM D5185r
	Titanium	ppm	ASTM D5185r
	Silver	ppm	ASTM D5185r
	Aluminum	ppm	ASTM D5185r
	Lead	ppm	ASTM D5185r
	Copper	ppm	ASTM D5185r
	Tin	ppm	ASTM D5185r
	Vanadium	ppm	ASTM D5185r
	White Metal	scalar	*Visual
	Yellow Metal	scalar	*Visual
CONTAMINATION	Silicon	ppm	ASTM D5185r
	Potassium	ppm	ASTM D5185r
The amount and size of particulates present in the system are	Water		WC Metho
acceptable. There is no indication of any contamination in the oil.	Particles >4µm		ASTM D764
	Particles >6µm		ASTM D764
	Particles >14µm		ASTM D764
	Particles >21µm		ASTM D764
	Particles >38µm		ASTM D764
	Particles >71µm		ASTM D764
	Oil Cleanliness		ISO 4406 (c
	Silt	scalar	*Visual
	Debris	scalar	*Visual
	Sand/Dirt	scalar	*Visual
	Appearance	scalar	*Visual
	Odor	scalar	*Visual
	Emulsified Water	scalar	*Visual
FLUID CONDITION	Sodium	ppm	ASTM D5185r
The AN level is acceptable for this fluid. The condition of the oil is	Boron	ppm	ASTM D5185r
suitable for further service.	Barium	ppm	ASTM D5185r
	Molybdenum	ppm	ASTM D5185r
	Manganese	ppm	ASTM D5185r
	Magnesium	ppm	ASTM D5185r
	Calcium	ppm	ASTM D5185r

_				()		
Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		LEC0039842		
Sample Date		Client Info		27 Jun 2023		
Machine Age	hrs	Client Info		414		
Oil Age	hrs	Client Info		414		
Filter Age	hrs	Client Info		414		
Oil Changed		Client Info		Not Changd		
Filter Changed		Client Info		Not Changd		
Sample Status				NORMAL		
PQ		ASTM D8184	>50	16		
Iron	ppm	ASTM D5185m	>32	<1		
Chromium	ppm	ASTM D5185m	>9	0		
Nickel	ppm	ASTM D5185m	>5	0		
Titanium	ppm	ASTM D5185m		0		
Silver	ppm	ASTM D5185m		0		
Aluminum	ppm	ASTM D5185m	>9	<1		
Lead	ppm	ASTM D5185m	>28	0		
Copper	ppm	ASTM D5185m	>50	2		
Tin	ppm	ASTM D5185m	>5	0		
Vanadium	ppm	ASTM D5185m		0		
White Metal	scalar	*Visual	NONE	NONE		
Yellow Metal	scalar	*Visual	NONE	NONE		
Silicon	ppm	ASTM D5185m	>11	0		
Potassium	ppm	ASTM D5185m	>20	1		
Water		WC Method	>0.075	NEG		
Particles >4µm		ASTM D7647	>80000	646		
Particles >6µm		ASTM D7647	>20000	156		
Particles >14µm		ASTM D7647	>640	16		
Particles >21µm		ASTM D7647	>160	7		
Particles >38µm		ASTM D7647	>40	0		
Particles >71µm		ASTM D7647	>10	0		
Oil Cleanliness		ISO 4406 (c)	>23/21/16	17/14/11		
Silt	scalar	*Visual	NONE	NONE		
Debris	scalar	*Visual	NONE	NONE		
Sand/Dirt	scalar	*Visual	NONE	NONE		
Appearance	scalar	*Visual	NORML	NORML		
Odor	scalar	*Visual	NORML	NORML		
Emulsified Water	scalar	*Visual	>0.075	NEG		
Sodium	ppm	ASTM D5185m	>21	<1		
Boron	ppm	ASTM D5185m		0		
Barium	ppm	ASTM D5185m		0		
Molybdenum	ppm	ASTM D5185m		0		
Manganese	ppm	ASTM D5185m		0		
Magnesium	ppm	ASTM D5185m		4		
Calcium	ppm	ASTM D5185m		16		
Phosphorus	ppm	ASTM D5185m	827	510		
Zinc	ppm	ASTM D5185m	0	36		
Sulfur	ppm	ASTM D5185m	13	172		
Acid Number (AN)	mg KOH/g	ASTM D8045	0.06	0.12		
Vice @ 10°C	~C+	ACTM DAAF	47	46.7		

Visc @ 40°C cSt ASTM D445 47

46.7



