



OIL ANALYSIS REPORT

WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL



Area
Store 8 - Pikeville
Machine Id
JOHN DEERE 850L 1T0850LXL MF390846
Component
Right Inner Final Drive
Fluid
JOHN DEERE HY-GARD HYD/TRANS (4 GAL)

RECOMMENDATION

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		LEC0042156	LEC0035800	LEC0033214
Sample Date		Client Info		10 Jul 2023	09 Feb 2023	24 Jun 2022
Machine Age	hrs	Client Info		1360	1022	650
Oil Age	hrs	Client Info		338	1022	650
Filter Age	hrs	Client Info		0	0	0
Oil Changed		Client Info		Changed	Changed	Not Changd
Filter Changed		Client Info		None	N/A	None
Sample Status				NORMAL	NORMAL	MARGINAL

WEAR

All component wear rates are normal.

PQ		ASTM D8184	>1250	26	31	34
Iron	ppm	ASTM D5185m	>750	21	45	32
Chromium	ppm	ASTM D5185m	>9	0	<1	<1
Nickel	ppm	ASTM D5185m	>10	0	<1	0
Titanium	ppm	ASTM D5185m		0	0	0
Silver	ppm	ASTM D5185m		0	0	0
Aluminum	ppm	ASTM D5185m	>40	1	<1	1
Lead	ppm	ASTM D5185m	>15	<1	1	1
Copper	ppm	ASTM D5185m	>40	<1	<1	<1
Tin	ppm	ASTM D5185m	>10	0	<1	0
Vanadium	ppm	ASTM D5185m		0	0	0
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE

CONTAMINATION







There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185m	>75	4	5	5
Potassium	ppm	ASTM D5185m	>20	2	0	<1
Water		WC Method	>0.075	NEG	NEG	NEG
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	▲ MODER
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.075	NEG	NEG	NEG

FLUID CONDITION

The condition of the oil is acceptable for the time in service.

Sodium	ppm	ASTM D5185m	>51	0	2	2
Boron	ppm	ASTM D5185m	6	0	0	4
Barium	ppm	ASTM D5185m	0	0	0	0
Molybdenum	ppm	ASTM D5185m	0	1	<1	<1
Manganese	ppm	ASTM D5185m		<1	1	<1
Magnesium	ppm	ASTM D5185m	145	97	95	96
Calcium	ppm	ASTM D5185m	3570	3487	3363	3319
Phosphorus	ppm	ASTM D5185m	1290	1043	881	962
Zinc	ppm	ASTM D5185m	1640	1231	1117	1126
Sulfur	ppm	ASTM D5185m		3832	3604	3237
Visc @ 40°C	cSt	ASTM D445	57.0	52.3	51.6	52.2



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : LEC0042156 **Received** : 12 Jul 2023
Lab Number : 05896423 **Tested** : 13 Jul 2023
Unique Number : 10552233 **Diagnosed** : 13 Jul 2023 - Don Baldrige
Test Package : CONST (Additional Tests: PQ)

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

LESLIE EQUIPMENT COMPANY
 105 TENNIS CENTER DR.
 MARIETTA, OH
 US 45750-9765
 Contact: LEANNE KENDALL
 KendalLeanne@lec1.com
 T:
 F: (740)373-5570