



OIL ANALYSIS REPORT

WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL

Area

{unassigned} [141874]

Machine Id

JOHN DEERE 245g 1FF245GXJKF801328

Component

Diesel Engine

Fluid

JOHN DEERE ENGINE OIL PLUS 50 II 15W40 (6 GAL)

RECOMMENDATION

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		LEC0040275	LEC0036935	LEC0027180
Sample Date		Client Info		08 Aug 2023	10 Feb 2023	04 Mar 2022
Machine Age	hrs	Client Info		3024	2555	1870
Oil Age	hrs	Client Info		469	685	436
Filter Age	hrs	Client Info		469	685	436
Oil Changed		Client Info		Changed	Changed	Changed
Filter Changed		Client Info		Changed	Changed	Changed
Sample Status				NORMAL	ABNORMAL	NORMAL

WEAR

All component wear rates are normal.

Iron	ppm	ASTM D5185m	>51	15	21	11
Chromium	ppm	ASTM D5185m	>11	0	<1	<1
Nickel	ppm	ASTM D5185m	>5	0	<1	0
Titanium	ppm	ASTM D5185m		0	0	0
Silver	ppm	ASTM D5185m	>3	<1	0	0
Aluminum	ppm	ASTM D5185m	>31	5	6	4
Lead	ppm	ASTM D5185m	>26	1	2	1
Copper	ppm	ASTM D5185m	>26	12	▲ 40	2
Tin	ppm	ASTM D5185m	>4	<1	2	<1
Vanadium	ppm	ASTM D5185m		0	0	0
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE

CONTAMINATION







There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185m	>120	10	14	10
Potassium	ppm	ASTM D5185m	>20	2	0	0
Fuel		WC Method	>2.1	<1.0	<1.0	<1.0
Water		WC Method	>0.21	NEG	NEG	NEG
Glycol		WC Method		NEG	NEG	NEG
Soot %	%	*ASTM D7844	>3	0.4	0.5	0.3
Nitration	Abs/cm	*ASTM D7624	>20	8.9	9.1	9.2
Sulfation	Abs/.1mm	*ASTM D7415	>30	22.8	23.7	23.1
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.21	NEG	NEG	NEG

FLUID CONDITION

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

Sodium	ppm	ASTM D5185m	>31	0	2	4
Boron	ppm	ASTM D5185m		233	213	211
Barium	ppm	ASTM D5185m		3	0	0
Molybdenum	ppm	ASTM D5185m		291	283	205
Manganese	ppm	ASTM D5185m		<1	1	<1
Magnesium	ppm	ASTM D5185m		852	854	735
Calcium	ppm	ASTM D5185m		1630	1593	1655
Phosphorus	ppm	ASTM D5185m		911	902	894
Zinc	ppm	ASTM D5185m		1162	1163	1054
Sulfur	ppm	ASTM D5185m		3058	3345	2605
Oxidation	Abs/.1mm	*ASTM D7414	>25	17.0	18.0	17.3
Base Number (BN)	mg KOH/g	ASTM D2896	13.6	9.1	9.0	9.5
Visc @ 100°C	cSt	ASTM D445	15.4	14.8	14.4	14.4



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : LEC0040275 **Received** : 14 Aug 2023
Lab Number : 05923254 **Tested** : 15 Aug 2023
Unique Number : 10603201 **Diagnosed** : 15 Aug 2023 - Wes Davis
Test Package : CONST (Additional Tests: TBN)

LESLIE EQUIPMENT COMPANY
 105 TENNIS CENTER DR.
 MARIETTA, OH
 US 45750-9765
 Contact: LEANNE KENDALL
 KendalLeanne@lec1.com

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

T:
F: (740)373-5570