



WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL

Machine Id
JOHN DEERE 350G 1FF350GXLFF810871
 Component
Hydraulic System
 Fluid
HITACHI HYDRAULIC SUPER EX 46HN (51 GAL)

RECOMMENDATION

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		JR0181145	JR0163450	JR0133117
Sample Date		Client Info		13 Aug 2023	29 Mar 2023	18 Jul 2022
Machine Age	hrs	Client Info		6933	6505	5567
Oil Age	hrs	Client Info		2429	6505	0
Filter Age	hrs	Client Info		0	0	0
Oil Changed		Client Info		Not Changd	Not Changd	N/A
Filter Changed		Client Info		Not Changd	Not Changd	N/A
Sample Status				NORMAL	NORMAL	ATTENTION

WEAR

All component wear rates are normal.

PQ		ASTM D8184	>50	17	6	18
Iron	ppm	ASTM D5185m	>32	20	2	17
Chromium	ppm	ASTM D5185m	>9	<1	<1	<1
Nickel	ppm	ASTM D5185m	>5	0	0	0
Titanium	ppm	ASTM D5185m		<1	0	<1
Silver	ppm	ASTM D5185m		0	0	0
Aluminum	ppm	ASTM D5185m	>9	3	<1	3
Lead	ppm	ASTM D5185m	>28	0	0	<1
Copper	ppm	ASTM D5185m	>50	1	<1	2
Tin	ppm	ASTM D5185m	>5	0	0	0
Vanadium	ppm	ASTM D5185m		0	0	0
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE

CONTAMINATION











The system cleanliness is acceptable for your target ISO 4406 cleanliness code. The system and fluid cleanliness is acceptable.

Silicon	ppm	ASTM D5185m	>11	6	2	4
Potassium	ppm	ASTM D5185m	>20	1	0	1
Water		WC Method	>0.075	NEG	NEG	NEG
Particles >4µm		ASTM D7647	>80000	77380	2876	▲ 106685
Particles >6µm		ASTM D7647	>20000	2831	372	5002
Particles >14µm		ASTM D7647	>640	56	17	45
Particles >21µm		ASTM D7647	>160	17	5	9
Particles >38µm		ASTM D7647	>40	1	0	0
Particles >71µm		ASTM D7647	>10	0	0	0
Oil Cleanliness		ISO 4406 (c)	>23/21/16	23/19/13	19/16/11	▲ 24/20/13
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.075	NEG	NEG	NEG

FLUID CONDITION

The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.

Sodium	ppm	ASTM D5185m	>21	0	0	0
Boron	ppm	ASTM D5185m		0	0	<1
Barium	ppm	ASTM D5185m		0	0	0
Molybdenum	ppm	ASTM D5185m		0	2	0
Manganese	ppm	ASTM D5185m		0	0	0
Magnesium	ppm	ASTM D5185m		<1	6	<1
Calcium	ppm	ASTM D5185m		5	30	7
Phosphorus	ppm	ASTM D5185m	827	482	495	488
Zinc	ppm	ASTM D5185m	0	33	75	52
Sulfur	ppm	ASTM D5185m	13	128	223	286
Acid Number (AN)	mg KOH/g	ASTM D8045	0.06	0.28	0.21	0.24
Visc @ 40°C	cSt	ASTM D445	47	44.4	46.9	44.0



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513

Sample No. : JR0181145

Lab Number : 05924768

Unique Number : 10604715

Test Package : CONST (Additional Tests: PQ)

Received : 15 Aug 2023

Tested : 16 Aug 2023

Diagnosed : 16 Aug 2023 - Jonathan Hester

JRE - GARNER

4161 AUBURN CHURCH RD

GARNER, NC

US 27529

Contact: ANDRE JELONEK

andre.jelonek@jamesriverequipment.com

T: (919)772-2121

F: (919)779-5432

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)