

WEAR NORMAL CONTAMINATION NORMAL FLUID CONDITION NORMAL



Area Store 3 - Norton Machine Id JOHN DEERE 250G 1FF250GXANF612025 Component

Component Swing Drive

JOHN DEERE GL-5 80W90 (2 GAL)

RECOMMENDATION	Test	UOM	Method	Limit/Abn	Current	History1	History2
Resample at the next service interval to monitor.	Sample Number	00111	Client Info	Linity ton	LEC0043051		
	Sample Date		Client Info		17 Aug 2023		
	Machine Age	hrs	Client Info		605		
	Oil Age	hrs	Client Info		605		
	Filter Age	hrs	Client Info		0		
	Oil Changed		Client Info		Changed		
	Filter Changed		Client Info		N/A		
	Sample Status				NORMAL		
WEAR	PQ		ASTM D8184		131		
All component wear rates are normal.	Iron	ppm	ASTM D5185m		132		
	Chromium	ppm	ASTM D5185m		2		
	Nickel	ppm	ASTM D5185m	>10	0		
	Titanium	ppm	ASTM D5185m		<1		
	Silver	ppm	ASTM D5185m		0		
	Aluminum	ppm	ASTM D5185m		<1		
	Lead	ppm	ASTM D5185m		0		
	Copper	ppm	ASTM D5185m		0		
	Tin	ppm	ASTM D5185m	>10	0		
	Vanadium	ppm	ASTM D5185m		0		
	White Metal	scalar	*Visual	NONE	NONE		
	Yellow Metal	scalar	*Visual	NONE	NONE		
CONTAMINATION	Silicon	ppm	ASTM D5185m	>31	22		
There is no indication of any contamination in the oil.	Potassium	ppm	ASTM D5185m		2		
	Water	le le	WC Method	>0.1	NEG		
	Silt	scalar	*Visual	NONE	NONE		
	Debris	scalar	*Visual	NONE	NONE		
	Sand/Dirt	scalar	*Visual	NONE	NONE		
	Appearance	scalar	*Visual	NORML	NORML		
	Odor	scalar	*Visual	NORML	NORML		
	Emulsified Water	scalar	*Visual	>0.1	NEG		
FLUID CONDITION	Sodium	ppm	ASTM D5185m	>51	2		
The condition of the oil is acceptable for the time in service.	Boron	ppm	ASTM D5185m		82		
	Barium	ppm	ASTM D5185m		3		
	Molybdenum	ppm	ASTM D5185m		0		
	Manganese	ppm	ASTM D5185m		2		
	Magnesium	ppm	ASTM D5185m		1		
	Calcium	ppm	ASTM D5185m		28		
	Phosphorus	ppm	ASTM D5185m		635		
	Zinc	ppm	ASTM D5185m		11		
	Sulfur	ppm	ASTM D5185m		21032		


Visc @ 40°C


cSt


ASTM D445

Submitted By: STORE 3 - NORTON - BRIAN YOUTZY

186







Submitted By: STORE 3 - NORTON - BRIAN YOUTZY