



OIL ANALYSIS REPORT

WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL

Machine Id
DEMAG PRESS 34 (S/N 7136-0092)
 Component
Hydraulic System
 Fluid
AW HYDRAULIC OIL ISO 68 (58 GAL)

RECOMMENDATION

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		WC0819559	WC0534560	WC0631180
Sample Date		Client Info		20 Jun 2023	25 Jun 2022	30 Oct 2021
Machine Age	mths	Client Info		0	0	0
Oil Age	mths	Client Info		0	0	0
Filter Age	mths	Client Info		0	0	0
Oil Changed		Client Info		N/A	N/A	N/A
Filter Changed		Client Info		N/A	N/A	N/A
Sample Status				NORMAL	NORMAL	NORMAL

WEAR

All component wear rates are normal.

Iron	ppm	ASTM D5185m	>20	5	6	7
Chromium	ppm	ASTM D5185m	>20	0	<1	<1
Nickel	ppm	ASTM D5185m	>20	0	0	0
Titanium	ppm	ASTM D5185m		0	0	0
Silver	ppm	ASTM D5185m		0	0	<1
Aluminum	ppm	ASTM D5185m	>20	2	<1	0
Lead	ppm	ASTM D5185m	>20	0	0	<1
Copper	ppm	ASTM D5185m	>20	6	6	6
Tin	ppm	ASTM D5185m	>20	0	0	<1
Vanadium	ppm	ASTM D5185m		0	0	0
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE

CONTAMINATION










The amount and size of particulates present in the system are acceptable. There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185m	>15	<1	<1	<1
Potassium	ppm	ASTM D5185m	>20	1	0	<1
Water		WC Method	>0.05	NEG	NEG	NEG
Particles >4µm		ASTM D7647		4166	1501	10152
Particles >6µm		ASTM D7647	>1300	1244	429	506
Particles >14µm		ASTM D7647	>160	131	50	28
Particles >21µm		ASTM D7647	>40	31	10	4
Particles >38µm		ASTM D7647	>10	1	1	0
Particles >71µm		ASTM D7647	>3	0	0	0
Oil Cleanliness		ISO 4406 (c)	>-/17/14	19/17/14	18/16/13	21/16/12
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.05	NEG	NEG	NEG

FLUID CONDITION

The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.

Sodium	ppm	ASTM D5185m		2	1	0
Boron	ppm	ASTM D5185m	5	0	0	<1
Barium	ppm	ASTM D5185m	5	0	0	0
Molybdenum	ppm	ASTM D5185m	5	0	0	0
Manganese	ppm	ASTM D5185m		0	<1	<1
Magnesium	ppm	ASTM D5185m	25	1	0	3
Calcium	ppm	ASTM D5185m	200	7	1	9
Phosphorus	ppm	ASTM D5185m	300	189	183	196
Zinc	ppm	ASTM D5185m	370	58	58	79
Sulfur	ppm	ASTM D5185m	2500	1289	1057	1073
Acid Number (AN)	mg KOH/g	ASTM D8045	0.57	0.17	0.19	0.219
Visc @ 40°C	cSt	ASTM D445	68	63.8	64.0	64.1



Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : WC0819559
Lab Number : 05939689
Unique Number : 10630301
Test Package : IND 2
Received : 31 Aug 2023
Tested : 01 Sep 2023
Diagnosed : 05 Sep 2023 - Don Baldrige

VIKING PLASTICS
 1 VIKING ST
 CORRY, PA
 US 16407
 Contact: TOM BURTON
 tburton@vikingplastics.com
 T: (814)664-8671
 F: (814)664-7797

Certificate L2367
 To discuss this sample report, contact Customer Service at 1-800-237-1369.
 * - Denotes test methods that are outside of the ISO 17025 scope of accreditation.
 Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)