



VOLVO

OIL ANALYSIS REPORT

WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL



Area
[44513]
 Machine Id
VOLVO A25G 752022
 Component
Diesel Engine
 Fluid
DIESEL ENGINE OIL SAE 15W40 (--- GAL)

RECOMMENDATION

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		VCP419610	VCP369840	VCP343646
Sample Date		Client Info		21 Apr 2023	03 Jan 2023	09 Feb 2022
Machine Age	hrs	Client Info		1939	1540	926
Oil Age	hrs	Client Info		0	0	0
Filter Age	hrs	Client Info		0	0	0
Oil Changed		Client Info		Changed	Changed	Changed
Filter Changed		Client Info		Changed	Changed	Changed
Sample Status				NORMAL	NORMAL	ABNORMAL

WEAR

All component wear rates are normal.

Iron	ppm	ASTM D5185m	>200	11	13	15
Chromium	ppm	ASTM D5185m	>20	<1	<1	<1
Nickel	ppm	ASTM D5185m	>10	<1	2	<1
Titanium	ppm	ASTM D5185m		0	0	<1
Silver	ppm	ASTM D5185m	>2	0	<1	<1
Aluminum	ppm	ASTM D5185m	>30	0	2	1
Lead	ppm	ASTM D5185m	>40	0	<1	<1
Copper	ppm	ASTM D5185m	>20	4	17	▲ 128
Tin	ppm	ASTM D5185m	>20	<1	1	1
Vanadium	ppm	ASTM D5185m		<1	0	0
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE

CONTAMINATION












There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185m	>20	5	6	9
Potassium	ppm	ASTM D5185m	>20	<1	0	<1
Fuel		WC Method	>3.0	<1.0	<1.0	0.5
Water		WC Method	>0.2	NEG	NEG	NEG
Glycol		WC Method		NEG	NEG	NEG
Soot %	%	*ASTM D7844	>3	0.3	0.3	0.3
Nitration	Abs/cm	*ASTM D7624	>20	8.1	7.3	7.6
Sulfation	Abs/.1mm	*ASTM D7415	>30	22.0	22.0	24.6
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG	NEG

FLUID CONDITION

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

Sodium	ppm	ASTM D5185m	>158	2	2	2
Boron	ppm	ASTM D5185m	250	34	32	32
Barium	ppm	ASTM D5185m	10	0	0	0
Molybdenum	ppm	ASTM D5185m	100	40	37	38
Manganese	ppm	ASTM D5185m		<1	<1	1
Magnesium	ppm	ASTM D5185m	450	518	501	477
Calcium	ppm	ASTM D5185m	3000	1821	1618	1776
Phosphorus	ppm	ASTM D5185m	1150	917	888	981
Zinc	ppm	ASTM D5185m	1350	1138	1105	1153
Sulfur	ppm	ASTM D5185m	4250	3679	3280	2681
Oxidation	Abs/.1mm	*ASTM D7414	>25	20.2	19.1	21.0
Base Number (BN)	mg KOH/g	ASTM D2896	8.5	10.0	9.8	10.3
Visc @ 100°C	cSt	ASTM D445	14.4	12.7	12.7	12.1



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : VCP419610 **Received** : 25 Sep 2023
Lab Number : 05959557 **Tested** : 26 Sep 2023
Unique Number : 10660770 **Diagnosed** : 26 Sep 2023 - Wes Davis
Test Package : MOB 1 (Additional Tests: TBN)

365 - ASCENDUM MACHINERY INC - SAVANNAH
 54 MEDLINE DR
 RICHMOND HILL, GA
 US 31324
 Contact: JESSE WILSON
 jesse.wilson@ascendummachinery.com

To discuss this sample report, contact Customer Service at 1-800-237-1369.
 * - Denotes test methods that are outside of the ISO 17025 scope of accreditation.
 Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012) F: (912)964-9515