



VOLVO

OIL ANALYSIS REPORT

WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL



Area
[607003]
Machine Id
VOLVO A40G 340676
Component
Diesel Engine
Fluid
VOLVO ULTRA DIESEL ENGINE OIL 15W40 VDS-3 (--- GAL)

RECOMMENDATION

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		VCP429157	VCP414116	VCP311191
Sample Date		Client Info		02 Oct 2023	30 Jun 2023	07 Aug 2021
Machine Age	hrs	Client Info		8783	8207	6025
Oil Age	hrs	Client Info		500	0	0
Filter Age	hrs	Client Info		0	0	0
Oil Changed		Client Info		Changed	Changed	Changed
Filter Changed		Client Info		Changed	Changed	Changed
Sample Status				NORMAL	NORMAL	ATTENTION

WEAR

All component wear rates are normal.

Iron	ppm	ASTM D5185m	>200	5	11	16
Chromium	ppm	ASTM D5185m	>20	<1	<1	<1
Nickel	ppm	ASTM D5185m	>10	<1	<1	<1
Titanium	ppm	ASTM D5185m		0	<1	<1
Silver	ppm	ASTM D5185m	>2	0	0	0
Aluminum	ppm	ASTM D5185m	>30	<1	2	3
Lead	ppm	ASTM D5185m	>40	0	0	1
Copper	ppm	ASTM D5185m	>20	1	6	14
Tin	ppm	ASTM D5185m	>20	0	<1	<1
Vanadium	ppm	ASTM D5185m		0	0	0
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE

CONTAMINATION











There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185m	>20	3	4	5
Potassium	ppm	ASTM D5185m	>20	0	0	1
Fuel		WC Method	>3.0	<1.0	<1.0	0.1
Water		WC Method	>0.2	NEG	NEG	NEG
Glycol		WC Method		NEG	NEG	NEG
Soot %	%	*ASTM D7844	>3	0.3	0.3	0.2
Nitration	Abs/cm	*ASTM D7624	>20	7.3	7.5	7.4
Sulfation	Abs/.1mm	*ASTM D7415	>30	19.0	20.1	17.7
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG	NEG

FLUID CONDITION

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

Sodium	ppm	ASTM D5185m		1	2	9
Boron	ppm	ASTM D5185m	2.5	<1	0	25
Barium	ppm	ASTM D5185m	0.0	0	0	0
Molybdenum	ppm	ASTM D5185m	0.7	60	56	13
Manganese	ppm	ASTM D5185m	0.0	<1	<1	<1
Magnesium	ppm	ASTM D5185m	256	992	928	203
Calcium	ppm	ASTM D5185m	2057	1104	1054	2051
Phosphorus	ppm	ASTM D5185m	935	1102	995	891
Zinc	ppm	ASTM D5185m	1223	1332	1214	1016
Sulfur	ppm	ASTM D5185m	4079	3265	3571	3212
Oxidation	Abs/.1mm	*ASTM D7414	>25	14.5	16.7	11.2
Base Number (BN)	mg KOH/g	ASTM D2896	10	8.7	8.7	---
Visc @ 100°C	cSt	ASTM D445	15.0	13.0	13.2	12.4



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : VCP429157 **Received** : 05 Oct 2023
Lab Number : 05970136 **Tested** : 05 Oct 2023
Unique Number : 10682086 **Diagnosed** : 09 Oct 2023 - Don Baldrige
Test Package : MOB 1 (Additional Tests: TBN)

BLAZE CONSTRUCTION
 5640 ST JEAN ST
 DETROIT, MI
 US 48213
 Contact: DAVE WARD
 dward@blazecontracting.net
 T: (248)632-2317
 F:

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)