

**WEAR** CONTAMINATION **FLUID CONDITION**  **NORMAL NORMAL NORMAL** 



## Machine Id CATERPILLAR 775F HAUL TRUCK 6151 (S/N DLS00524)

CATERPILLAR 7/5F HAU Component Rear Left Differential	L TRUCK 6	151	(S/N DI	_500	524)		
{not provided} ( GAL)							
RECOMMENDATION	Test	UOM	Method	Limit/Abn	Current	History1	History2
TECOMMENDATION	Sample Number	OCIVI	Client Info	LIIIIUAUII	TO10002736		
Resample at the next service interval to monitor. Please specify the brand, type, and viscosity of the oil on your next sample.	Sample Date		Client Info		29 Sep 2023		
	Machine Age	hrs	Client Info		542		
	Oil Age	hrs	Client Info		542		
	Filter Age	hrs	Client Info		0		
	Oil Changed	1113	Client Info		Not Change		
	Filter Changed		Client Info		None		
	Sample Status				NORMAL		
					·····		
WEAR	PQ		ASTM D8184		42		
All component wear rates are normal.	Iron	ppm	ASTM D5185m	>500	42		
	Chromium	ppm	ASTM D5185m	>3	<1		
	Nickel	ppm	ASTM D5185m	>3	0		
	Titanium	ppm	ASTM D5185m	>2	<1		
	Silver	ppm	ASTM D5185m	>2	0		
	Aluminum	ppm	ASTM D5185m	>30	2		
	Lead	ppm	ASTM D5185m	>13	1		
	Copper	ppm	ASTM D5185m	>103	4		
	Tin	ppm	ASTM D5185m	>5	<1		
	Vanadium	ppm	ASTM D5185m		0		
	White Metal	scalar	*Visual	NONE	NONE		
	Yellow Metal	scalar	*Visual	NONE	NONE		
CONTAMINATION	Silicon		ACTM DE10Em	. 100	25	[	
There is no indication of any contamination in the oil.		ppm	ASTM D5185m		35 3		
	Potassium Water	ppm	ASTM D5185m WC Method		NEG		
	Silt	scalar	*Visual	NONE	NONE		
	Debris	scalar	*Visual	NONE	NONE		
	Sand/Dirt	scalar	*Visual	NONE	NONE		
	Appearance	scalar	*Visual	NORML	NORML		
	Odor	scalar	*Visual	NORML	NORML		
	Emulsified Water		*Visual	>.2	NEG		
FLUID CONDITION	Sodium	ppm	ASTM D5185m		5		
Viscosity of sample indicates oil is within ISO 220 range, advise investigate. Confirm oil type. The AN level is acceptable for this fluid.	Boron	ppm	ASTM D5185m		3		
	Barium	ppm	ASTM D5185m		0		
	Molybdenum	ppm	ASTM D5185m		2		
	Manganese	ppm	ASTM D5185m		<1		
	Magnesium	ppm	ASTM D5185m		26		
	Calcium	ppm	ASTM D5185m		2716		
	Phosphorus	ppm	ASTM D5185m		943		
	Zinc	ppm	ASTM D5185m		1149		
	Sulfur	ppm	ASTM D5185m		4368		
	Acid Number (AN)	mg KOH/g	ASTM D8045		1.09		
	Visc @ 40°C	cSt	ASTM D445		197		
	Vice @ 1000C	~C+	ACTM DATE		475	I .	


Visc @ 100°C cSt

Viscosity Index (VI) Scale ASTM D2270

ASTM D445

17.5

95





Certificate L2367

Laboratory Sample No. Lab Number

**Unique Number** 

: 05972272 : 10684222

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 Recieved : 06 Oct 2023 : TO10002736 Diagnosed : 10 Oct 2023 Diagnostician : Angela Borella

Test Package : MOB 2 ( Additional Tests: KV100, PQ, VI )

\* - Denotes test methods that are outside of the ISO 17025 scope of accreditation. Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

To discuss this sample report, contact Customer Service at 1-800-237-1369.

**ANCHOR STONE TULSA ROCK** 

TULSA ROCK QUARRY, 66TH ST N 145TH AVENUE

TULSA, OK US 74137

Contact: SKIP SAENGERHAUSEN skip@anchorstoneco.com

T: (918)928-4575

F: