



WEAR CONTAMINATION FLUID CONDITION

NORMAL NORMAL NORMAL


Area

Store 8 - Pikeville [RO#144058] JOHN DEERE 210G 1FF210GXENF530277

Swing Drive

JOHN DEERE GL-5 80W90 (2 GAL)

JOHN DEERE GL-5 80W90 (2 GA	7 /						
RECOMMENDATION	Test	UOM	Method	Limit/Abn	Current	History1	History2
Resample at the next service interval to monitor.	Sample Number		Client Info		LEC0042027	LEC0040377	
	Sample Date		Client Info		16 Oct 2023	19 Apr 2023	
	Machine Age	hrs	Client Info		1064	435	
	Oil Age	hrs	Client Info		1064	435	
	Filter Age	hrs	Client Info		0	0	
	Oil Changed		Client Info		Changed	Not Changd	
	Filter Changed		Client Info		N/A	N/A	
	Sample Status				NORMAL	NORMAL	
WEAR	PQ		ASTM D8184		65	89	
All component wear rates are normal.	Iron	ppm	ASTM D5185m	>151	134	106	
	Chromium	ppm	ASTM D5185m		<1	1	
	Nickel	ppm	ASTM D5185m		0	0	
	Titanium	ppm	ASTM D5185m		<1	0	
	Silver	ppm	ASTM D5185m		0	0	
	Aluminum	ppm	ASTM D5185m	>21	2	<1	
	Lead	ppm	ASTM D5185m	>51	0	0	
	Copper	ppm	ASTM D5185m	>51	<1	<1	
	Tin	ppm	ASTM D5185m	>10	0	0	
	Vanadium	ppm	ASTM D5185m		0	0	
	White Metal	scalar	*Visual	NONE	NONE	NONE	
	Yellow Metal	scalar	*Visual	NONE	NONE	NONE	
CONTAMINATION	Silicon	ppm	ASTM D5185m	>31	15	13	
There is no indication of any contamination in the fluid.	Potassium	ppm	ASTM D5185m	>20	3	<1	
	Water		WC Method	>0.1	NEG	NEG	
	Silt	scalar	*Visual	NONE	NONE	NONE	
	Debris	scalar	*Visual	NONE	NONE	NONE	
	Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	
	Appearance	scalar	*Visual	NORML	NORML	NORML	
	Odor	scalar	*Visual	NORML	NORML	NORML	
	Emulsified Water	scalar	*Visual	>0.1	NEG	NEG	
FLUID CONDITION	Sodium	ppm	ASTM D5185m	>51	0	2	
The condition of the fluid is acceptable for the time in service.	Boron	ppm	ASTM D5185m		74	76	
	Barium	ppm	ASTM D5185m		8	5	
	Molybdenum	ppm	ASTM D5185m		<1	<1	
	Manganese	ppm	ASTM D5185m		3	3	
	Magnesium	ppm	ASTM D5185m		1	1	
	Calcium	ppm	ASTM D5185m		31	26	
	Phosphorus	ppm	ASTM D5185m		481	502	
	Zinc	ppm	ASTM D5185m		12	11	
	Sulfur	ppm	ASTM D5185m		17355	17358	
	Gallai	le le					







Certificate L2367

Laboratory Sample No.

Lab Number : 05985059 Unique Number : 10702354

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 : LEC0042027

Received **Tested** Diagnosed Test Package : CONST (Additional Tests: PQ)

: 23 Oct 2023 : 23 Oct 2023 - Don Baldridge

: 20 Oct 2023

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

LESLIE EQUIPMENT COMPANY

105 TENNIS CENTER DR. MARIETTA, OH US 45750-9765

Contact: LEANNE KENDALL KendalLeanne@lec1.com

> T: F: (740)373-5570

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)