
**WEAR CONTAMINATION FLUID CONDITION** 

NORMAL **ABNORMAL NORMAL** 

## **MATTEI 10026468 - PRO QUIP**

Component Compressor

{not provided} ( GAL)							
RECOMMENDATION	Test	UOM	Method	Limit/Abn	Current	History1	History2
No corrective action is recommended at this time. Resample at the next service interval to monitor.	Sample Number		Client Info		AN36452		
	Sample Date		Client Info		11 Oct 2023		
	Machine Age	hrs	Client Info		0		
	Oil Age	hrs	Client Info		0		
	Filter Age	hrs	Client Info		0		
	Oil Changed		Client Info		N/A		
	Filter Changed		Client Info		N/A		
	Sample Status				ABNORMAL		
WEAR	lua-a		ACTM DE105	F0	_		
WEAR	Iron	ppm	ASTM D5185m		5		
All component wear rates are normal.	Chromium	ppm	ASTM D5185m	>10	0		
	Nickel	ppm	ASTM D5185m		<1		
	Titanium	ppm	ASTM D5185m		0		
	Silver	ppm	ASTM D5185m	٥٢	0		
	Aluminum	ppm	ASTM D5185m		1		
	Lead	ppm	ASTM D5185m		<1		
	Copper	ppm	ASTM D5185m		<1		
	Tin	ppm	ASTM D5185m	>15	1		
	Vanadium	ppm	ASTM D5185m		0		
	White Metal	scalar	*Visual	NONE	NONE		
	Yellow Metal	scalar	*Visual	NONE	NONE		
CONTAMINATION	Silicon	ppm	ASTM D5185m	>25	<b>▲</b> 53		
Elemental level of silicon (Si) above normal. The water content is negligible.	Potassium	ppm	ASTM D5185m		2		
	Water	%	ASTM D6304	>0.1	0.084		
	ppm Water	ppm	ASTM D6304		843.4		
	Silt	scalar	*Visual	NONE	NONE		
	Debris	scalar	*Visual	NONE	NONE		
	Sand/Dirt	scalar	*Visual	NONE	NONE		
	Appearance	scalar	*Visual	NORML	NORML		
	Odor	scalar	*Visual	NORML	NORML		
	<b>Emulsified Water</b>		*Visual	>0.1	NEG		
FLUID CONDITION	Sodium	ppm	ASTM D5185m		6		
The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.	Boron	ppm	ASTM D5185m		0		
	Barium	ppm	ASTM D5185m		0		
	Molybdenum	ppm	ASTM D5185m		0		
	Manganese	ppm	ASTM D5185m		<1		
	Magnesium	ppm	ASTM D5185m		6		
	Calcium	ppm	ASTM D5185m		15		
	Phosphorus	ppm	ASTM D5185m		893		
	Zinc	ppm	ASTM D5185m		38		
			ASTM D5185m		40		
	Sulfur	ppm	ASTIVI DOTOSIII		48		
	Sulfur Acid Number (AN)	mg KOH/g	ASTM D3163111 ASTM D8045		0.32		







Certificate L2367

Laboratory Sample No.

: AN36452 Lab Number : 05985646 Unique Number : 10702941 Test Package : IND 2

: WearCheck USA - 501 Madison Ave., Cary, NC 27513

Received **Tested** 

: 20 Oct 2023 : 24 Oct 2023

: 25 Oct 2023 - Jonathan Hester Diagnosed

US 21133 Contact: MARTY WARD jward@matteicomp.com T: (410)521-7020

RANDALLSTOWN, MD

9635 LIBERTY ROAD, SUITE E

To discuss this sample report, contact Customer Service at 1-800-237-1369. \* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

F: (410)521-7024