



WEAR CONTAMINATION FLUID CONDITION

NORMAL NORMAL NORMAL



Store 9 - Marietta

JOHN DEERE 210G 1FF210GXKNF530270

Swing Drive

JOHN DEERE GL-5 80W90 (2	GAL)						
RECOMMENDATION	Test	UOM	Method	Limit/Abn	Current	History1	History2
Resample at the next service interval to monitor.	Sample Number		Client Info		LEC0045425	LEC0042310	
	Sample Date		Client Info		16 Oct 2023	19 Jun 2023	
	Machine Age	hrs	Client Info		906	340	
	Oil Age	hrs	Client Info		906	340	
	Filter Age	hrs	Client Info		0	0	
	Oil Changed		Client Info		Changed	Not Changd	
	Filter Changed		Client Info		None	Not Changd	
	Sample Status				NORMAL	NORMAL	
WEAR	PQ		ASTM D8184		34	35	
All component wear rates are normal.	Iron	ppm	ASTM D5185m	>151	83	65	
	Chromium	ppm	ASTM D5185m	>11	1	<1	
	Nickel	ppm	ASTM D5185m	>10	0	0	
	Titanium	ppm	ASTM D5185m		0	0	
	Silver	ppm	ASTM D5185m		0	0	
	Aluminum	ppm	ASTM D5185m	>21	<1	1	
	Lead	ppm	ASTM D5185m	>51	0	0	
	Copper	ppm	ASTM D5185m		<1	<1	
	Tin	ppm	ASTM D5185m	>10	0	0	
	Vanadium	ppm	ASTM D5185m		0	<1	
	White Metal	scalar	*Visual	NONE	NONE	NONE	
	Yellow Metal	scalar	*Visual	NONE	NONE	NONE	
CONTAMINATION There is no indication of any contamination in the oil.	Silicon	ppm	ASTM D5185m	>31	15	13	
	Potassium	ppm	ASTM D5185m	>20	1	2	
	Water		WC Method	>0.1	NEG	NEG	
	Silt	scalar	*Visual	NONE	NONE	NONE	
	Debris	scalar	*Visual	NONE	NONE	NONE	
	Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	
	Appearance	scalar	*Visual	NORML	NORML	NORML	
	Odor	scalar	*Visual	NORML	NORML	NORML	
	Emulsified Water	scalar	*Visual	>0.1	NEG	NEG	
FLUID CONDITION	Sodium	ppm	ASTM D5185m	>51	<1	2	
The condition of the oil is acceptable for the time in service.	Boron	ppm	ASTM D5185m		75	74	
	Barium	ppm	ASTM D5185m		5	0	
	Molybdenum	ppm	ASTM D5185m		0	0	
	Manganese	ppm	ASTM D5185m		2	2	
	Magnesium	ppm	ASTM D5185m		2	<1	
	Calcium	ppm	ASTM D5185m		65	44	
	Phosphorus	ppm	ASTM D5185m		510	509	
	Zinc	ppm	ASTM D5185m		24	2	
	Sulfur	ppm	ASTM D5185m		15991	18121	
	Visc @ 40°C	cSt	ASTM D445	1	187	187	







Laboratory Sample No.

: LEC0045425 Lab Number : 05988384

Unique Number : 10711046

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 Received : 24 Oct 2023

Tested : 26 Oct 2023 Diagnosed : 26 Oct 2023 - Don Baldridge

Test Package : CONST (Additional Tests: PQ)

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

To discuss this sample report, contact Customer Service at 1-800-237-1369.

105 TENNIS CENTER DR.

MARIETTA, OH US 45750-9765 Contact: LEANNE KENDALL

LESLIE EQUIPMENT COMPANY

KendalLeanne@lec1.com T:

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

F: (740)373-5570