



OIL ANALYSIS REPORT

WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL

Machine Id
HAITIAN PRESS 55 (S/N 201507012032608)
 Component
Hydraulic System
 Fluid
AW HYDRAULIC OIL ISO 68 (67 GAL)

RECOMMENDATION

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		WC0768408	WC0534569	WC0534529
Sample Date		Client Info		19 Oct 2023	22 Oct 2022	10 Oct 2021
Machine Age	mths	Client Info		0	0	0
Oil Age	mths	Client Info		0	0	0
Filter Age	mths	Client Info		0	0	0
Oil Changed		Client Info		N/A	N/A	N/A
Filter Changed		Client Info		N/A	N/A	N/A
Sample Status				NORMAL	NORMAL	ABNORMAL

WEAR

All component wear rates are normal.

Iron	ppm	ASTM D5185m	>20	2	1	1
Chromium	ppm	ASTM D5185m	>20	<1	0	0
Nickel	ppm	ASTM D5185m	>20	0	0	0
Titanium	ppm	ASTM D5185m		0	0	0
Silver	ppm	ASTM D5185m		0	0	1
Aluminum	ppm	ASTM D5185m	>20	2	0	0
Lead	ppm	ASTM D5185m	>20	<1	<1	1
Copper	ppm	ASTM D5185m	>20	25	22	25
Tin	ppm	ASTM D5185m	>20	0	0	0
Vanadium	ppm	ASTM D5185m		0	0	0
White Metal	scalar	*Visual	NONE	NONE	VLITE	▲ LIGHT
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE

CONTAMINATION










There is no indication of any contamination in the oil. The amount and size of particulates present in the system are acceptable.

Silicon	ppm	ASTM D5185m	>15	0	3	4
Potassium	ppm	ASTM D5185m	>20	1	<1	0
Water		WC Method	>0.05	NEG	NEG	NEG
Particles >4µm		ASTM D7647		677	6077	11398
Particles >6µm		ASTM D7647	>1300	176	1283	▲ 2692
Particles >14µm		ASTM D7647	>160	19	108	▲ 209
Particles >21µm		ASTM D7647	>40	5	31	40
Particles >38µm		ASTM D7647	>10	0	3	4
Particles >71µm		ASTM D7647	>3	0	0	0
Oil Cleanliness		ISO 4406 (c)	>-/17/14	17/15/11	20/17/14	▲ 21/19/15
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	VLITE	LIGHT
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.05	NEG	NEG	NEG

FLUID CONDITION

The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.

Sodium	ppm	ASTM D5185m		0	0	0
Boron	ppm	ASTM D5185m	5	0	0	0
Barium	ppm	ASTM D5185m	5	3	0	0
Molybdenum	ppm	ASTM D5185m	5	<1	0	0
Manganese	ppm	ASTM D5185m		0	<1	<1
Magnesium	ppm	ASTM D5185m	25	<1	0	<1
Calcium	ppm	ASTM D5185m	200	36	38	48
Phosphorus	ppm	ASTM D5185m	300	294	298	343
Zinc	ppm	ASTM D5185m	370	318	359	429
Sulfur	ppm	ASTM D5185m	2500	1118	1589	1081
Acid Number (AN)	mg KOH/g	ASTM D8045	0.57	0.22	0.23	0.223
Visc @ 40°C	cSt	ASTM D445	68	46.5	45.7	48.6



Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : WC0768408 **Received** : 25 Oct 2023
Lab Number : 05989120 **Tested** : 27 Oct 2023
Unique Number : 10711782 **Diagnosed** : 27 Oct 2023 - Don Baldrige
Test Package : IND 2

VIKING PLASTICS
 1 VIKING ST
 CORY, PA
 US 16407
 Contact: TOM BURTON
 tburton@vikingplastics.com
 T: (814)664-8671
 F: (814)664-7797

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)