


WEAR CONTAMINATION FLUID CONDITION **NORMAL NORMAL NORMAL**

Store 5 - Cross Lanes

JOHN DEERE 700L 1T0700LXKPF446100

Left Final Drive

	TRANS (3 GA	<u> </u>					
RECOMMENDATION	Test	UOM	Method	Limit/Abn	Current	History1	History2
Resample at the next service interval to monitor.	Sample Number		Client Info		LEC0043255		
	Sample Date		Client Info		25 Oct 2023		
	Machine Age	hrs	Client Info		442		
	Oil Age	hrs	Client Info		442		
	Filter Age	hrs	Client Info		0		
	Oil Changed		Client Info		Not Changd		
	Filter Changed		Client Info		N/A		
	Sample Status				NORMAL		
WEAR	PQ		ASTM D8184	>1250	67		
	Iron	ppm	ASTM D5185m		87		
All component wear rates are normal.	Chromium	ppm	ASTM D5185m		2		
	Nickel	ppm	ASTM D5185m		<1		
	Titanium	ppm	ASTM D5185m		<1		
	Silver	ppm	ASTM D5185m		0		
	Aluminum	ppm	ASTM D5185m	>40	<1		
	Lead	ppm	ASTM D5185m	>15	0		
	Copper	ppm	ASTM D5185m	>40	0		
	Tin	ppm	ASTM D5185m	>10	<1		
	Vanadium	ppm	ASTM D5185m		0		
	White Metal	scalar	*Visual	NONE	NONE		
	Yellow Metal	scalar	*Visual	NONE	NONE		
CONTAMINATION There is no indication of any contamination in the oil.	Silicon	ppm	ASTM D5185m	>75	20		
	Potassium	ppm	ASTM D5185m		2		
	Water	le le	WC Method		NEG		
	Silt	scalar	*Visual	NONE	NONE		
	Debris	scalar	*Visual	NONE	NONE		
	Sand/Dirt	scalar	*Visual	NONE	NONE		
	Appearance	scalar	*Visual	NORML	NORML		
	Odor	scalar	*Visual	NORML	NORML		
	Emulsified Water	scalar	*Visual	>0.075	NEG		
FLUID CONDITION	Sodium	ppm	ASTM D5185m	<u>-51</u>	4		
	Boron	ppm	ASTM D5185m		2		
			ASTM D5185m		0		
The condition of the oil is acceptable for the time in service.	Barium						
The condition of the oil is acceptable for the time in service.	Barium Molybdenum	ppm					
The condition of the oil is acceptable for the time in service.	Molybdenum	ppm	ASTM D5185m		<1		
The condition of the oil is acceptable for the time in service.	Molybdenum Manganese	ppm	ASTM D5185m ASTM D5185m	0	<1 3		
The condition of the oil is acceptable for the time in service.	Molybdenum Manganese Magnesium	ppm ppm	ASTM D5185m ASTM D5185m ASTM D5185m	145	<1		
The condition of the oil is acceptable for the time in service.	Molybdenum Manganese	ppm	ASTM D5185m ASTM D5185m	0 145 3570	<1 3 68		
The condition of the oil is acceptable for the time in service.	Molybdenum Manganese Magnesium Calcium	ppm ppm ppm	ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m	0 145 3570 1290	<1 3 68 3015		
The condition of the oil is acceptable for the time in service.	Molybdenum Manganese Magnesium Calcium Phosphorus	ppm ppm ppm ppm	ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m	0 145 3570 1290	<1 3 68 3015 871	 	





Laboratory Sample No.

: WearCheck USA - 501 Madison Ave., Cary, NC 27513

Lab Number : 05991793 Unique Number : 10714455

: LEC0043255

Received **Tested** Diagnosed

: 30 Oct 2023 : 30 Oct 2023 - Sean Felton Test Package : CONST (Additional Tests: PQ)

: 27 Oct 2023

To discuss this sample report, contact Customer Service at 1-800-237-1369. * - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

105 TENNIS CENTER DR. MARIETTA, OH US 45750-9765 Contact: LEANNE KENDALL

KendalLeanne@lec1.com

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

F: (740)373-5570