



OIL ANALYSIS REPORT

WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL

Machine Id
EAST BAILER
 Component
Hydraulic System
 Fluid
AW HYDRAULIC OIL ISO 32 (--- GAL)

RECOMMENDATION

Resample at the next service interval to monitor. Please specify the component make and model with your next sample.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		PTK0000391	PTK0001307	PTK0001282
Sample Date		Client Info		09 Nov 2023	13 Jun 2023	23 Nov 2022
Machine Age	wks	Client Info		0	0	0
Oil Age	wks	Client Info		0	0	0
Filter Age	wks	Client Info		0	0	0
Oil Changed		Client Info		N/A	N/A	N/A
Filter Changed		Client Info		N/A	N/A	N/A
Sample Status				NORMAL	NORMAL	NORMAL

WEAR

All component wear rates are normal.

Iron	ppm	ASTM D5185m	>20	0	<1	0
Chromium	ppm	ASTM D5185m	>10	<1	1	1
Nickel	ppm	ASTM D5185m	>10	0	0	0
Titanium	ppm	ASTM D5185m		0	<1	0
Silver	ppm	ASTM D5185m		0	0	0
Aluminum	ppm	ASTM D5185m	>10	0	0	<1
Lead	ppm	ASTM D5185m	>10	0	0	0
Copper	ppm	ASTM D5185m	>75	5	5	5
Tin	ppm	ASTM D5185m	>10	0	0	<1
Vanadium	ppm	ASTM D5185m		0	0	0
White Metal	scalar	*Visual	NONE	NONE	LIGHT	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE

CONTAMINATION










The system cleanliness is acceptable for your target ISO 4406 cleanliness code. The system and fluid cleanliness is acceptable.

Silicon	ppm	ASTM D5185m	>20	<1	0	1
Potassium	ppm	ASTM D5185m	>20	0	1	0
Water		WC Method	>0.1	NEG	NEG	NEG
Particles >4µm		ASTM D7647		1973	2302	740
Particles >6µm		ASTM D7647	>2500	636	671	166
Particles >14µm		ASTM D7647	>320	108	95	18
Particles >21µm		ASTM D7647	>80	36	36	5
Particles >38µm		ASTM D7647	>20	1	3	0
Particles >71µm		ASTM D7647	>4	0	0	0
Oil Cleanliness		ISO 4406 (c)	>18/15	16/14	17/14	15/11
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.1	NEG	NEG	NEG

FLUID CONDITION

The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.

Sodium	ppm	ASTM D5185m		1	0	1
Boron	ppm	ASTM D5185m	5	0	0	0
Barium	ppm	ASTM D5185m	5	0	2	0
Molybdenum	ppm	ASTM D5185m	5	0	<1	<1
Manganese	ppm	ASTM D5185m		0	0	0
Magnesium	ppm	ASTM D5185m	25	1	2	1
Calcium	ppm	ASTM D5185m	200	51	57	57
Phosphorus	ppm	ASTM D5185m	300	311	321	349
Zinc	ppm	ASTM D5185m	370	429	430	428
Sulfur	ppm	ASTM D5185m	2500	1130	1215	1356
Acid Number (AN)	mg KOH/g	ASTM D8045	0.57	0.18	0.27	0.24
Visc @ 40°C	cSt	ASTM D445	32	31.5	31.1	30.7



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513

Sample No. : PTK0000391

Lab Number : 06017317

Unique Number : 10756461

Test Package : MOB 2

Received : 24 Nov 2023

Tested : 28 Nov 2023

Diagnosed : 28 Nov 2023 - Wes Davis

GRAPHIC PACKAGING

1500 NICHOLAS BLVD

ELK GROVE, IL

US 60017

Contact: TONY HILDY

anthonyhildy@graphicpkg.com

T: (847)437-1700

F:

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)