



WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL

Machine Id
HBR
Component
Starboard Main Engine
Fluid
CHEVRON DELO 400 XLE 15W40 (11 GAL)

RECOMMENDATION

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		MW06028310	MW06017179	MW05981732
Sample Date		Client Info		06 Dec 2023	23 Nov 2023	16 Oct 2023
Machine Age	hrs	Client Info		26654	26071	25690
Oil Age	hrs	Client Info		960	381	434
Filter Age	hrs	Client Info		0	0	0
Oil Changed		Client Info		N/A	N/A	N/A
Filter Changed		Client Info		N/A	N/A	N/A
Sample Status				NORMAL	NORMAL	NORMAL

WEAR

All component wear rates are normal.

Iron	ppm	ASTM D5185m	>75	6	6	6
Chromium	ppm	ASTM D5185m	>8	<1	<1	<1
Nickel	ppm	ASTM D5185m	>2	0	<1	<1
Titanium	ppm	ASTM D5185m	>3	<1	<1	<1
Silver	ppm	ASTM D5185m	>2	0	0	0
Aluminum	ppm	ASTM D5185m	>15	2	2	3
Lead	ppm	ASTM D5185m	>18	0	0	0
Copper	ppm	ASTM D5185m	>80	<1	<1	1
Tin	ppm	ASTM D5185m	>14	0	0	<1
Vanadium	ppm	ASTM D5185m		0	0	<1
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE

CONTAMINATION







There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185m	>20	7	6	5
Potassium	ppm	ASTM D5185m	>20	2	2	2
Fuel		WC Method	>4.0	<1.0	<1.0	<1.0
Water		WC Method	>0.1	NEG	NEG	NEG
Glycol		WC Method		NEG	NEG	NEG
Soot %	%	*ASTM D7844		1.1	1	1
Nitration	Abs/cm	*ASTM D7624	>20	6.6	6.5	6.7
Sulfation	Abs/.1mm	*ASTM D7415	>30	22.3	22.4	22.5
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.1	NEG	NEG	NEG

FLUID CONDITION

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

Sodium	ppm	ASTM D5185m	>75	0	<1	0
Boron	ppm	ASTM D5185m		332	316	358
Barium	ppm	ASTM D5185m		6	0	10
Molybdenum	ppm	ASTM D5185m		109	103	109
Manganese	ppm	ASTM D5185m		0	<1	<1
Magnesium	ppm	ASTM D5185m		489	470	495
Calcium	ppm	ASTM D5185m		1710	1581	1542
Phosphorus	ppm	ASTM D5185m	760	806	698	823
Zinc	ppm	ASTM D5185m	830	954	921	972
Sulfur	ppm	ASTM D5185m	2770	2956	2958	2869
Oxidation	Abs/.1mm	*ASTM D7414	>25	14.5	14.3	15.0
Base Number (BN)	mg KOH/g	ASTM D2896	10.7	8.4	7.9	8.1
Visc @ 100°C	cSt	ASTM D445	14.9	13.4	13.6	13.5



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : MW06028310
Lab Number : 06028310
Unique Number : 10778101
Test Package : MAR 2
Received : 07 Dec 2023
Tested : 09 Dec 2023
Diagnosed : 09 Dec 2023 - Wes Davis

ILLINOIS MARINE TOWING
 PO BOX 391
 LEMONT, IL
 US 60439
 Contact: RHETT DANIEL
 rdaniel@imtowing.com
 T: (630)280-4926
 F: (630)739-2041

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)