


Machine Id **KIOTI CK2610SE PAOGA0005** Component Diesel Engine ~ ~ . .

ļ	٢	(ľ	ί	J			I		l)	V	N	•	4	•	J		(-	-	-	1	ί	Ā	ŀ	4	J)			
•	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	7	-	-	-	-	-	-	-	-	-	-	٤	-	-	-

RECOMMENDATION	Test	UOM	Method	Limit/Abn	Current	History1	History2
Resample at the next service interval to monitor.	Sample Number		Client Info		KT0000752		
·····	Sample Date		Client Info		29 Nov 2023		
	Machine Age	hrs	Client Info		93		
	Oil Age	hrs	Client Info		93		
	Filter Age	hrs	Client Info		93		
	Oil Changed		Client Info		Not Changd		
	Filter Changed		Client Info		Not Changd		
	Sample Status				NORMAL		
WEAR	Iron	ppm	ASTM D5185m	>100	32		
	Chromium	ppm	ASTM D5185m	>20	<1		
Metal levels are typical for a components first oil change.	Nickel	ppm	ASTM D5185m	>4	0		
	Titanium	ppm	ASTM D5185m		0		
	Silver	ppm	ASTM D5185m	>3	0		
	Aluminum	ppm	ASTM D5185m		23		
	Lead	ppm	ASTM D5185m		8		
	Copper	ppm	ASTM D5185m		39		
	Tin	ppm	ASTM D5185m		2		
	Vanadium	ppm	ASTM D5185m	-	0		
	White Metal	scalar	*Visual	NONE	NONE		
	Yellow Metal	scalar	*Visual	NONE	NONE		
CONTAMINATION	Silicon	ppm	ASTM D5185m		10		
There is no indication of any contamination in the oil	Potassium	ppm	ASTM D5185m	>20	<1		
There is no indication of any contamination in the oil.	Fuel		WC Method	>5	<1.0		
	Water		WC Method	>0.2	NEG		
	Glycol		WC Method		NEG		
	Soot %	%	*ASTM D7844	>3	0.1		
	Nitration	Abs/cm	*ASTM D7624	>20	5.0		
	Sulfation	Abs/.1mm	*ASTM D7415	>30	13.3		
	Silt	scalar	*Visual	NONE	NONE		
	Debris	scalar	*Visual	NONE	NONE		
	Sand/Dirt	scalar	*Visual	NONE	NONE		
	Appearance	scalar	*Visual	NORML	NORML		
	Odor	scalar	*Visual	NORML	NORML		
	Emulsified Water	scalar	*Visual	>0.2	NEG		
FLUID CONDITION	Sodium	ppm	ASTM D5185m		4		
I LOID CONDITION	Boron		ASTM D5185m		12		
The BN result indicates that there is suitable alkalinity remaining in the	Barium	ppm ppm	ASTM D5185m		0		
oil. The condition of the oil is suitable for further service.	Molybdenum	ppm	ASTM D5185m		15		
	Manganese	ppm	ASTM D5185m		<1		
	Magnesium	ppm	ASTM D5185m		549		
	Calcium	ppm	ASTM D5185m		924		
	Phosphorus	ppm	ASTM D5185m		712		
	Zinc	ppm	ASTM D5185m		939		
	Sulfur	ppm	ASTM D5185m		2883		
	Oxidation	Abs/.1mm	*ASTM D5185111	>25	7.4		
	Base Number (BN)	mg KOH/g	ASTM D7414 ASTM D2896	>LJ	6.1		
	Visc @ 100°C	cSt	ASTM D2090 ASTM D445				
		COL	ASTIVI D445		11.6		



16 15.

15

14

13.5

11


12.5 12

11.5 1

10.5

cSt (100°C) 14 !





Contact/Location: JASON ATKINSON - SHFROG