

LONGVIEW **LEGACY 154360**

Right Pump Drive

TULCO LUBSOIL 4220 SYN GEAR 220 (120 GAL)

TOLCO LODGOIL 4220 STN GLAN 220 (120 G	ARL)						
RECOMMENDATION	Test	UOM	Method	Limit/Abn	Current	History1	History2
Resample at the next service interval to monitor.	Sample Number		Client Info		TO50002045		
	Sample Date		Client Info		18 Dec 2023		
	Machine Age	hrs	Client Info		9257		
	Oil Age	hrs	Client Info		0		
	Filter Age	hrs	Client Info		1253		
	Oil Changed		Client Info		Not Changd		
	Filter Changed		Client Info		Changed		
	Sample Status				NORMAL		
WEAR	PQ		ASTM D8184		16		
	Iron	nnm	ASTM D0104 ASTM D5185m	> 150	33		
All component wear rates are normal.	Chromium	ppm	ASTM D5185m				
	Nickel	ppm ppm	ASTM D5185m		3		
	Titanium		ASTM D5185m	>10	-3 <1		
	Silver	ppm ppm	ASTM D5185m		0		
	Aluminum		ASTM D5185m	>25	14		
	Lead	ppm ppm	ASTM D5185m		2		
	Copper		ASTM D5185m		3		
	Tin	ppm ppm	ASTM D5185m		2		
	Vanadium	ppm	ASTM D5105m ASTM D5185m	>10	0		
	White Metal	scalar	*Visual	NONE	NONE		
	Yellow Metal	scalar	*Visual	NONE	NONE		
			, , , , , , , , , , , , , , , , , , ,				
CONTAMINATION	Silicon	ppm	ASTM D5185m	>50	7		
There is no indication of any contamination in the oil.	Potassium	ppm	ASTM D5185m	>20	<1		
	Water		WC Method	>0.1	NEG		
	Silt	scalar	*Visual	NONE	NONE		
	Debris	scalar	*Visual	NONE	LIGHT		
	Sand/Dirt	scalar	*Visual	NONE	NONE		
	Appearance	scalar	*Visual	NORML	NORML		
	Odor	scalar	*Visual	NORML	NORML		
	Emulsified Water	scalar	*Visual	>0.1	NEG		
FLUID CONDITION	Sodium	ppm	ASTM D5185m		0		
The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.	Boron	ppm	ASTM D5185m		0		
	Barium	ppm	ASTM D5185m		0		
	Molybdenum	ppm	ASTM D5185m		347		
	Manganese	ppm	ASTM D5185m		<1		
	Magnesium	ppm	ASTM D5185m		2		
	Calcium	ppm	ASTM D5185m		3		
	Phosphorus	ppm	ASTM D5185m	230	677		
	Zinc	ppm	ASTM D5185m	200	28		
	Sulfur	ppm	ASTM D5185m	2530	21309		
	Acid Number (AN)		ASTM D5165III		0.94		
	Visc @ 40°C	cSt	ASTM D0045 ASTM D445		79.9		
	130 @ 40 0	001	A011010440	212	13.5		

Visc @ 100°C cSt


Viscosity Index (VI) Scale ASTM D2270 146

--- ---

10.4

113

ASTM D445 24.7



KLX ENERGY SERVICES Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513 Sample No. Recieved : 21 Dec 2023 5104 ESTES PKWY : TO50002045 Lab Number : 06042257 LONGVIEW, TX Diagnosed : 26 Dec 2023 : 10802865 Diagnostician : Jonathan Hester US 75603 Unique Number Test Package : IND 2 (Additional Tests: KV100, PQ, VI) Contact: DUSTIN TREST Certificate L2367 dustin.trest@klx.com To discuss this sample report, contact Customer Service at 1-800-237-1369. * - Denotes test methods that are outside of the ISO 17025 scope of accreditation. T: F: Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

B