



WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL

Machine Id
AGC
Component
Starboard Main Engine
Fluid
CHEVRON DELO 400 XLE 15W40 (--- GAL)

RECOMMENDATION

Resample at the next service interval to monitor. Please specify the component make and model with your next sample.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		MW06048291	MW06017175	MW06017163
Sample Date		Client Info		01 Jan 2024	23 Nov 2023	23 Nov 2023
Machine Age	hrs	Client Info		60621	59998	59283
Oil Age	hrs	Client Info		623	715	560
Filter Age	hrs	Client Info		0	0	0
Oil Changed		Client Info		N/A	N/A	N/A
Filter Changed		Client Info		N/A	N/A	N/A
Sample Status				NORMAL	NORMAL	MARGINAL

WEAR

All component wear rates are normal.

Iron	ppm	ASTM D5185m	>75	1	2	0
Chromium	ppm	ASTM D5185m	>8	0	<1	0
Nickel	ppm	ASTM D5185m	>2	0	<1	<1
Titanium	ppm	ASTM D5185m	>3	<1	2	<1
Silver	ppm	ASTM D5185m	>2	0	0	0
Aluminum	ppm	ASTM D5185m	>15	2	2	2
Lead	ppm	ASTM D5185m	>18	0	0	<1
Copper	ppm	ASTM D5185m	>80	<1	1	<1
Tin	ppm	ASTM D5185m	>14	<1	0	<1
Vanadium	ppm	ASTM D5185m		0	0	<1
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE

CONTAMINATION







There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185m	>20	4	4	3
Potassium	ppm	ASTM D5185m	>20	1	2	3
Fuel		WC Method	>4.0	<1.0	<1.0	0.7
Water		WC Method	>0.1	NEG	NEG	NEG
Glycol		WC Method		NEG	NEG	NEG
Soot %	%	*ASTM D7844		0.1	0.1	0.1
Nitration	Abs/cm	*ASTM D7624	>20	6.3	6.2	5.6
Sulfation	Abs/.1mm	*ASTM D7415	>30	21.7	20.9	18.0
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.1	NEG	NEG	NEG

FLUID CONDITION

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

Sodium	ppm	ASTM D5185m	>75	<1	<1	2
Boron	ppm	ASTM D5185m		269	248	205
Barium	ppm	ASTM D5185m		0	0	0
Molybdenum	ppm	ASTM D5185m		99	83	46
Manganese	ppm	ASTM D5185m		<1	<1	<1
Magnesium	ppm	ASTM D5185m		558	496	280
Calcium	ppm	ASTM D5185m		1593	1378	1677
Phosphorus	ppm	ASTM D5185m	760	699	663	937
Zinc	ppm	ASTM D5185m	830	999	883	1027
Sulfur	ppm	ASTM D5185m	2770	2760	3040	3251
Oxidation	Abs/.1mm	*ASTM D7414	>25	16.2	15.1	12.0
Base Number (BN)	mg KOH/g	ASTM D2896	10.7	7.9	7.8	7.7
Visc @ 100°C	cSt	ASTM D445	14.9	13.1	13.1	▲ 12.4



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513

Sample No. : MW06048291

Lab Number : 06048291

Unique Number : 10808899

Test Package : MAR 2

Received : 29 Dec 2023

Tested : 02 Jan 2024

Diagnosed : 02 Jan 2024 - Wes Davis

ILLINOIS MARINE TOWING

PO BOX 391

LEMONT, IL

US 60439

Contact: RHETT DANIEL

rdaniel@imtowing.com

T: (630)280-4926

F: (630)739-2041

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)