
**WEAR CONTAMINATION FLUID CONDITION** 

**NORMAL NORMAL** NORMAL

## JOHN DEERE 7760 1N07760XJB0035205

Component Rear Differential

GEAR OIL SAE 80W140 ( GAL)							
RECOMMENDATION	Test	UOM	Method	Limit/Abn	Current	History1	History2
Resample at the next service interval to monitor. The fluid was not specified, however, a fluid match indicates that this fluid is (GENERIC) GEAR OIL SAE 80W140. Please confirm.	Sample Number		Client Info		JR0201867		
	Sample Date		Client Info		07 Jan 2024		
	Machine Age	hrs	Client Info		2250		
	Oil Age	hrs	Client Info		0		
	Filter Age	hrs	Client Info		0		
	Oil Changed		Client Info		N/A		
	Filter Changed		Client Info		N/A		
	Sample Status				NORMAL		
WEAR	PQ		ASTM D8184		206		
All component wear rates are normal.	Iron	ppm	ASTM D5185m	>500	315		
	Chromium	ppm	ASTM D5185m	>10	3		
	Nickel	ppm	ASTM D5185m	>10	0		
	Titanium	ppm	ASTM D5185m		0		
	Silver	ppm	ASTM D5185m		0		
	Aluminum	ppm	ASTM D5185m	>25	0		
	Lead	ppm	ASTM D5185m	>25	18		
	Copper	ppm	ASTM D5185m	>100	30		
	Tin	ppm	ASTM D5185m	>10	2		
	Vanadium	ppm	ASTM D5185m		0		
	White Metal	scalar	*Visual	NONE	NONE		
	Yellow Metal	scalar	*Visual	NONE	NONE		
CONTAMINATION	Silicon	ppm	ASTM D5185m	>75	27		
There is no indication of any contamination in the oil.	Potassium	ppm	ASTM D5185m	>20	10		
	Water		WC Method	>.2	NEG		
	Silt	scalar	*Visual	NONE	NONE		
	Debris	scalar	*Visual	NONE	NONE		
	Sand/Dirt	scalar	*Visual	NONE	NONE		
	Appearance	scalar	*Visual	NORML	NORML		
	Odor	scalar	*Visual	NORML	NORML		
	Emulsified Water	scalar	*Visual	>.2	NEG		
FLUID CONDITION	Sodium	ppm	ASTM D5185m		12		
The condition of the oil is acceptable for the time in service.	Boron	ppm	ASTM D5185m		180		
	Barium	ppm	ASTM D5185m		0		
	Molybdenum	ppm	ASTM D5185m	12	11		
	Manganese	ppm	ASTM D5185m	10	8		
	Magnesium	ppm	ASTM D5185m		2		
	Calcium	ppm	ASTM D5185m		26		
	Phosphorus	ppm	ASTM D5185m		1011		
	Zinc Sulfur	ppm	ASTM D5185m ASTM D5185m	22500	18 27610		
	Visc @ 40°C	ppm cSt	ASTM D3163III	263	27610 270		
Report Id: IAMWAK (WLISCAR) 0605/267 (Generated: 01/09/202/ 17:51:10) Rev. 1	V130 @ 40 0	COL	70 INI D440				 2 - IAMMAK





Laboratory

Sample No. Lab Number **Unique Number** 

: JR0201867 : 06054267 : 10820216

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 Recieved : 08 Jan 2024 Diagnosed Diagnostician : Wes Davis Test Package : CONST ( Additional Tests: PQ )

: 09 Jan 2024

WAKEFIELD, VA Contact: BILL ACKER

To discuss this sample report, contact Customer Service at 1-800-237-1369. backer@jamesriverequipment.com \* - Denotes test methods that are outside of the ISO 17025 scope of accreditation. T: (757)899-3232 Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012) F: (757)899-6464

US 23888

JRE - WAKEFIELD

10489 GENERAL MAHONE HWY