



WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL

Machine Id
V117
 Component
Rear Differential
 Fluid
GEAR OIL SAE 80W140 (--- GAL)

RECOMMENDATION

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		JR0193350	JR0171760	JR0115595
Sample Date		Client Info		05 Dec 2023	26 Jun 2023	06 Jun 2022
Machine Age	mls	Client Info		160799	149603	138170
Oil Age	mls	Client Info		34555	23359	5541
Filter Age	mls	Client Info		0	0	0
Oil Changed		Client Info		Not Changed	Not Changed	Not Changed
Filter Changed		Client Info		Changed	N/A	N/A
Sample Status				NORMAL	NORMAL	NORMAL

WEAR

All component wear rates are normal.

PQ		ASTM D8184		70	102	116
Iron	ppm	ASTM D5185m	>500	330	371	457
Chromium	ppm	ASTM D5185m	>10	2	2	3
Nickel	ppm	ASTM D5185m	>10	8	7	3
Titanium	ppm	ASTM D5185m		3	4	8
Silver	ppm	ASTM D5185m		0	0	<1
Aluminum	ppm	ASTM D5185m	>25	2	4	4
Lead	ppm	ASTM D5185m	>25	<1	0	<1
Copper	ppm	ASTM D5185m	>100	1	2	1
Tin	ppm	ASTM D5185m	>10	0	0	0
Vanadium	ppm	ASTM D5185m		0	<1	0
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE

CONTAMINATION







There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185m	>75	11	10	10
Potassium	ppm	ASTM D5185m	>20	7	7	9
Water		WC Method	>.2	NEG	NEG	NEG
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>.2	NEG	NEG	NEG

FLUID CONDITION

The condition of the oil is acceptable for the time in service.

Sodium	ppm	ASTM D5185m		0	3	<1
Boron	ppm	ASTM D5185m	400	182	227	242
Barium	ppm	ASTM D5185m	200	8	0	0
Molybdenum	ppm	ASTM D5185m	12	30	31	28
Manganese	ppm	ASTM D5185m		10	10	9
Magnesium	ppm	ASTM D5185m	12	2	0	3
Calcium	ppm	ASTM D5185m	150	20	47	18
Phosphorus	ppm	ASTM D5185m	1650	997	1030	976
Zinc	ppm	ASTM D5185m	125	10	21	10
Sulfur	ppm	ASTM D5185m	22500	20463	22807	16096
Visc @ 40°C	cSt	ASTM D445	263	252	253	256



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : JR0193350 **Received** : 08 Jan 2024
Lab Number : 06054271 **Diagnosed** : 09 Jan 2024
Unique Number : 10820220 **Diagnostician** : Don Baldrige
Test Package : CONST (Additional Tests: PQ)

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

MATTHEWS CONSTRUCTION
 127 GRAYSON RD
 ROCK HILL, SC
 US 29732
 Contact: Tad Clinton
 tclinton@matthewsconstructionco.com
 T: (803)207-5607
 F: