


WEAR CONTAMINATION FLUID CONDITION

NORMAL NORMAL NORMAL

[SW1028121 ODDONETTO] **VOLVO A40G 340471**

Component Drop Box

GEAR OIL SAE 75W80 (GAL)							
RECOMMENDATION	Test	UOM	Method	Limit/Abn	Current	History1	History2
Resample at the next service interval to monitor.	Sample Number		Client Info		VCP430503	VCP316314	
	Sample Date		Client Info		29 Dec 2023	15 Jul 2021	
	Machine Age	hrs	Client Info		8301	7149	
	Oil Age	hrs	Client Info		0	0	
	Filter Age	hrs	Client Info		0	0	
	Oil Changed		Client Info		Changed	Not Changd	
	Filter Changed		Client Info		N/A	N/A	
	Sample Status				NORMAL	NORMAL	
WEAR	Iron	ppm	ASTM D5185m	>500	70	51	
All component wear rates are normal.	Chromium	ppm	ASTM D5185m	>20	1	<1	
	Nickel	ppm	ASTM D5185m		<1	<1	
	Titanium	ppm	ASTM D5185m		<1	0	
	Silver	ppm	ASTM D5185m		0	0	
	Aluminum	ppm	ASTM D5185m	>30	4	5	
	Lead	ppm	ASTM D5185m	>30	<1	0	
	Copper	ppm	ASTM D5185m	>30	2	<1	
	Tin	ppm	ASTM D5185m	>20	<1	<1	
	Vanadium	ppm	ASTM D5185m		0	0	
	White Metal	scalar	*Visual	NONE	NONE	NONE	
	Yellow Metal	scalar	*Visual	NONE	NONE	NONE	
CONTAMINATION	Silicon	ppm	ASTM D5185m	>50	5	4	
There is no indication of any contamination in the oil.	Potassium	ppm	ASTM D5185m		1	0	
	Water		WC Method	>0.2	NEG	NEG	
	Silt	scalar	*Visual	NONE	NONE	NONE	
	Debris	scalar	*Visual	NONE	NONE	NONE	
	Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	
	Appearance	scalar	*Visual	NORML	NORML	NORML	
	Odor	scalar	*Visual	NORML	NORML	NORML	
	Emulsified Water	scalar	*Visual	>0.2	NEG	NEG	
FLUID CONDITION	Sodium	ppm	ASTM D5185m		0	5	
	Boron	ppm	ASTM D5185m	400	174	295	
The condition of the oil is acceptable for the time in service.	Barium	ppm	ASTM D5185m		7	0	
	Molybdenum	ppm	ASTM D5185m	12	2	2	
	Manganese	ppm	ASTM D5185m		1	<1	
	Magnesium	ppm	ASTM D5185m	12	4	5	
	Calcium	ppm	ASTM D5185m	150	48	57	
	Phosphorus	ppm	ASTM D5185m	1650	1564	2147	
	Zinc	ppm	ASTM D5185m	125	25	42	
	Sulfur	ppm	ASTM D5185m	22500	23364	23995	
	Visc @ 40°C	cSt	ASTM D445	48	44.1	54.7	







Certificate L2367

Laboratory Sample No. Lab Number **Unique Number**

: VCP430503 : 06054370 : 10820319 Test Package : MOB 1

To discuss this sample report, contact Customer Service at 1-800-237-1369.

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 : 08 Jan 2024 Recieved : 09 Jan 2024 Diagnosed : Wes Davis Diagnostician

ARNOLD MACHINERY COMPANY 4323 EAST WINSLOW AVENUE PHOENIX, AZ

> Contact: RANDY PRZEKURAT randyp@arnoldmachinery.com T:

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation. Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

F: (602)414-1904

US 85040