WEAR CONTAMINATION FLUID CONDITION

NORMAL NORMAL


Area [RSO036579]

VOLVO A45G 352532



Component Transmission (Auto)

RECOMMENDATION	Test	UOM	Method	Limit/Abn	Current	History1	History2
Resample at the next service interval to monitor.	Sample Number		Client Info		VCP430859		
	Sample Date		Client Info		02 Jan 2024		
	Machine Age	hrs	Client Info		5101		
	Oil Age	hrs	Client Info		0		
	Filter Age	hrs	Client Info		0		
	Oil Changed		Client Info		Changed		
	Filter Changed		Client Info		Changed		
	Sample Status				NORMAL		
WEAR	Iron	ppm	ASTM D5185m	>160	52		
All component wear rates are normal.	Chromium	ppm	ASTM D5185m	>5	<1		
	Nickel	ppm	ASTM D5185m	>5	9		
	Titanium	ppm	ASTM D5185m		<1		
	Silver	ppm	ASTM D5185m	>5	0		
	Aluminum	ppm	ASTM D5185m	>50	20		
	Lead	ppm	ASTM D5185m	>50	<1		
	Copper	ppm	ASTM D5185m	>225	53		
	Tin	ppm	ASTM D5185m	>10	8		
	Vanadium	ppm	ASTM D5185m		0		
	White Metal	scalar	*Visual	NONE	NONE		
	Yellow Metal	scalar	*Visual	NONE	NONE		
CONTAMINATION	Silicon	ppm	ASTM D5185m	>20	8		
	Potassium	ppm	ASTM D5185m		3		
There is no indication of any contamination in the fluid.	Water	ррпп	WC Method	>0.1	NEG		
	Silt	scalar	*Visual	NONE	NONE		
	Debris	scalar	*Visual	NONE	NONE		
	Sand/Dirt	scalar	*Visual	NONE	NONE		
	Appearance	scalar	*Visual	NORML	NORML		
	Odor	scalar	*Visual	NORML	NORML		
	Emulsified Water	scalar	*Visual	>0.1	NEG		
FLUID CONDITION	Sodium	ppm	ASTM D5185m		2		
The condition of the fluid is acceptable for the time in service.	Boron	ppm	ASTM D5185m	187	74		
	Barium	ppm	ASTM D5185m		0		
	Molybdenum	ppm	ASTM D5185m		1		
	Manganese	ppm	ASTM D5185m		2		
	Magnesium	ppm	ASTM D5185m		2		
	Calcium	ppm	ASTM D5185m		79		
	Phosphorus	ppm	ASTM D5185m		204		
	Zinc	ppm	ASTM D5185m	56	0		
	Sulfur	ppm	ASTM D5185m	1336	2082		
	Visc @ 40°C	cSt	ASTM D445		28.5		







Certificate L2367

Report Id: VOLVO8247 [WUSCAR] 06054454 (Generated: 01/10/2024 09:04:03) Rev: 1

Laboratory Sample No. Lab Number **Unique Number**

: VCP430859 : 06054454 : 10820403 Test Package : MOB 1 To discuss this sample report, contact Customer Service at 1-800-237-1369.

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 Recieved : 08 Jan 2024 : 10 Jan 2024 Diagnosed : Sean Felton Diagnostician

COWIN EQUIPMENT COMPANY

7950 PITTMAN AVE PENSACOLA, FL US 32534 Contact: HUGH DOBBS HDOBBS@COWIN.COM T: (850)479-3004

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation. Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

F: (850)474-1602