WEAR CONTAMINATION **FLUID CONDITION**

NORMAL SEVERE ABNORMAL

Machine Id

QSK 19

Component

| ŀ | l | r | 1 | C |) | t | ı | 0 | ľ | • | 0 | ١ | / | Ī | C | ı | е | (| t | ł | | (| - | - | - | | (| 3 | ! | | ξ | Š |) | |
|-----|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|--|
| - ' | = | - | - | - | - | - | - | - | - | - | - | - | - | - | - | - | - | - | - | = | - | - | - | - | - | - | - | - | - | - | - | - | • | |

| Component Diesel Engine | | | | | | | |
|---|------------------|----------|-------------|----------------|-------------|----------|----------|
| {not provided} (QTS) | | | | | | | |
| RECOMMENDATION | Test | UOM | Method | Limit/Abn | Current | History1 | History2 |
| HECOMMENDATION | Sample Number | OOW | Client Info | LITTIU/ADIT | LF0001760 | | |
| We advise that you check the fuel injection system. We recommend | Sample Date | | Client Info | | 07 Jan 2024 | | |
| that you drain the oil from the component if this has not already been | Machine Age | hrs | Client Info | | 0 | | |
| done. We recommend an early resample to monitor this condition. | Oil Age | hrs | Client Info | | 0 | | |
| Please specify the component make and model with your next sample. Please specify the brand, type, and viscosity of the oil on your next | Filter Age | hrs | Client Info | | 0 | | |
| sample. | Oil Changed | | Client Info | | N/A | | |
| | Filter Changed | | Client Info | | N/A | | |
| | Sample Status | | | | SEVERE | | |
| WEAR | Iron | ppm | ASTM D5185m | >100 | 50 | | |
| WEAT | Chromium | ppm | ASTM D5185m | | 2 | | |
| All component wear rates are normal. | Nickel | ppm | ASTM D5185m | | <1 | | |
| | Titanium | ppm | ASTM D5185m | 77 | <1 | | |
| | Silver | ppm | ASTM D5185m | >3 | 0 | | |
| | Aluminum | ppm | ASTM D5185m | | 1 | | |
| | Lead | | ASTM D5185m | | 4 | | |
| | Copper | ppm | ASTM D5185m | | 17 | | |
| | Tin | ppm | ASTM D5185m | | <1 | | |
| | Vanadium | ppm | ASTM D5185m | 710 | 0 | | |
| | White Metal | scalar | *Visual | NONE | NONE | | |
| | Yellow Metal | scalar | *Visual | NONE | NONE | | |
| | | | | | | | |
| CONTAMINATION | Silicon | ppm | ASTM D5185m | >25 | 6 | | |
| There is a high amount of fuel present in the oil. Tests confirm the | Potassium | ppm | ASTM D5185m | | 2 | | |
| presence of fuel in the oil. | Fuel | % | ASTM D3524 | | 10.6 | | |
| p | Water | | WC Method | >0.2 | NEG | | |
| | Glycol | | WC Method | | NEG | | |
| | Soot % | % | *ASTM D7844 | | 0.1 | | |
| | Nitration | Abs/cm | *ASTM D7624 | >20 | 6.6 | | |
| | Sulfation | Abs/.1mm | | | 18.0 | | |
| | Silt | scalar | *Visual | NONE | NONE | | |
| | Debris | scalar | *Visual | NONE | NONE | | |
| | Sand/Dirt | scalar | *Visual | NONE | NONE | | |
| | Appearance | scalar | *Visual | NORML | NORML | | |
| | Odor | scalar | *Visual | NORML | NORML | | |
| | Emulsified Water | scalar | *Visual | >0.2 | NEG | | |
| FLUID CONDITION | Sodium | ppm | ASTM D5185m | | 2 | | |
| 1 Edib GONDITION | Boron | ppm | ASTM D5185m | | 136 | | |
| The BN result indicates that there is suitable alkalinity remaining in the | Barium | ppm | ASTM D5185m | | 0 | | |
| oil. Fuel is present in the oil and is lowering the viscosity. The oil is no | Molybdenum | ppm | ASTM D5185m | | 18 | | |
| longer serviceable due to the presence of contaminants. | Manganese | ppm | ASTM D5185m | | 1 | | |
| | Magnesium | ppm | ASTM D5185m | | 662 | | |
| | Calcium | ppm | ASTM D5185m | | 1246 | | |
| | Phosphorus | ppm | ASTM D5185m | | 780 | | |
| | Zinc | ppm | ASTM D5185m | | 902 | | |
| | Sulfur | ppm | ASTM D5185m | | 3037 | | |
| | Oxidation | Abs/.1mm | *ASTM D7414 | >25 | 12.4 | | |
| | Base Number (BN) | | | | 8.2 | | |
| | Visc @ 100°C | cSt | ASTM D445 | | 10.6 | | |
| | - | | | | | | |





Laboratory Sample No. Lab Number **Unique Number**

: LF0001760

: 06054558 : 10820507

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 Recieved : 08 Jan 2024 Diagnosed : 12 Jan 2024 Diagnostician : Wes Davis

Test Package : MOB 1 (Additional Tests: FuelDilution, PercentFuel, TBN) To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation. Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012) **D PALMER & SONS**

139 BEACH LAKE HWY HONESDALE, PA US 18431

Contact: CHRIS DOWNEY palmernsons@verizon.net

T: (570)253-1618 F: (570)253-9147