



WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL

Machine Id
820016-101300

Component
Diesel Engine

Fluid
PETRO CANADA DURON SHP 15W40 (--- GAL)

RECOMMENDATION

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		GFL0078290	GFL0080049	GFL0028599
Sample Date		Client Info		02 Jan 2024	04 Oct 2023	14 Feb 2022
Machine Age	hrs	Client Info		12381	11754	9156
Oil Age	hrs	Client Info		0	217	450
Filter Age	hrs	Client Info		0	217	450
Oil Changed		Client Info		Not Changd	Not Changd	Changed
Filter Changed		Client Info		Changed	Not Changd	Changed
Sample Status				NORMAL	NORMAL	NORMAL

WEAR

All component wear rates are normal.

Iron	ppm	ASTM D5185m	>100	23	9	0
Chromium	ppm	ASTM D5185m	>20	<1	<1	<1
Nickel	ppm	ASTM D5185m	>4	<1	0	0
Titanium	ppm	ASTM D5185m		0	<1	0
Silver	ppm	ASTM D5185m	>3	0	0	3
Aluminum	ppm	ASTM D5185m	>20	13	8	2
Lead	ppm	ASTM D5185m	>40	<1	0	<1
Copper	ppm	ASTM D5185m	>330	2	1	<1
Tin	ppm	ASTM D5185m	>15	<1	<1	0
Vanadium	ppm	ASTM D5185m		0	<1	0
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE

CONTAMINATION







There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185m	>25	6	3	2
Potassium	ppm	ASTM D5185m	>20	35	19	<1
Fuel		WC Method	>5	<1.0	<1.0	<1.0
Water		WC Method	>0.2	NEG	NEG	NEG
Glycol		WC Method		NEG	NEG	NEG
Soot %	%	*ASTM D7844	>3	0.4	0.2	0.2
Nitration	Abs/cm	*ASTM D7624	>20	6.8	6.4	5.6
Sulfation	Abs/.1mm	*ASTM D7415	>30	19.8	18.7	18.6
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG	NEG

FLUID CONDITION

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

Sodium	ppm	ASTM D5185m		2	3	3
Boron	ppm	ASTM D5185m	0	6	<1	2
Barium	ppm	ASTM D5185m	0	0	12	0
Molybdenum	ppm	ASTM D5185m	60	66	59	53
Manganese	ppm	ASTM D5185m	0	2	<1	0
Magnesium	ppm	ASTM D5185m	1010	979	937	854
Calcium	ppm	ASTM D5185m	1070	1159	1019	1256
Phosphorus	ppm	ASTM D5185m	1150	1183	990	1029
Zinc	ppm	ASTM D5185m	1270	1373	1210	1301
Sulfur	ppm	ASTM D5185m	2060	3398	2965	2814
Oxidation	Abs/.1mm	*ASTM D7414	>25	15.8	14.8	13.1
Base Number (BN)	mg KOH/g	ASTM D2896	9.8	8.5	7.9	9.8
Visc @ 100°C	cSt	ASTM D445	15.4	14.7	14.1	13.4



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : GFL0078290 **Received** : 08 Jan 2024
Lab Number : 06054622 **Diagnosed** : 09 Jan 2024
Unique Number : 10820571 **Diagnostician** : Wes Davis
Test Package : FLEET

GFL Environmental - 844 - Princeton Hauling
 10129 Highway 62 West
 Princeton, KY
 US 42445
 Contact: ROBERT THIBAUT
 robert.thibault@gflenv.com
 T: (931)237-6045
 F:

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)