**WEAR CONTAMINATION FLUID CONDITION** 

**NORMAL ABNORMAL NORMAL** 

## [LOGGERHEAD FARMS]


## **JOHN DEERE 843L-II 1DW843LBTMF711551**

Component Hydraulic System

Hydraulic System   							
RECOMMENDATION	Test	UOM	Method	Limit/Abn	Current	History1	History2
We recommend you service the filters on this component. Resample at the next service interval to monitor. We were unable to perform a particle count due to a high concentration of particles present in this sample.	Sample Number		Client Info		JR0164588		
	Sample Date		Client Info		05 Jan 2024		
	Machine Age	hrs	Client Info		4049		
	Oil Age	hrs	Client Info		4049		
	Filter Age	hrs	Client Info		4049		
	Oil Changed		Client Info		N/A		
	Filter Changed		Client Info		N/A		
	Sample Status				ABNORMAL		
WEAR	PQ		ASTM D8184		12		
All component wear rates are normal.	Iron	ppm	ASTM D5185m	>20	0		
	Chromium	ppm	ASTM D5185m	>10	0		
	Nickel	ppm	ASTM D5185m	>10	0		
	Titanium	ppm	ASTM D5185m		0		
	Silver	ppm	ASTM D5185m		0		
	Aluminum	ppm	ASTM D5185m		0		
	Lead	ppm	ASTM D5185m	>10	0		
	Copper	ppm	ASTM D5185m	>75	4		
	Tin	ppm	ASTM D5185m	>10	0		
	Vanadium	ppm	ASTM D5185m		0		
	White Metal	scalar	*Visual	NONE	NONE		
	Yellow Metal	scalar	*Visual	NONE	NONE		
CONTAMINATION	Silicon	ppm	ASTM D5185m	>20	<1		
Moderate concentration of visible dirt/debris present in the oil.	Potassium	ppm	ASTM D5185m	>20	<1		
	Water		WC Method	>0.1	NEG		
	Silt	scalar	*Visual	NONE	NONE		
	Debris	scalar	*Visual	NONE	▲ MODER		
	Sand/Dirt	scalar	*Visual	NONE	NONE		
	Appearance	scalar	*Visual	NORML	NORML		
	Odor	scalar	*Visual	NORML	NORML		
	Emulsified Water	scalar	*Visual	>0.1	NEG		
FLUID CONDITION	Sodium	ppm	ASTM D5185m		2		
The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.	Boron	ppm	ASTM D5185m		<1		
	Barium	ppm	ASTM D5185m		0		
	Molybdenum	ppm	ASTM D5185m		0		
	Manganese	ppm	ASTM D5185m		0		
	Magnesium	ppm	ASTM D5185m		8		
	Calcium	ppm	ASTM D5185m		2301		
	Phosphorus	ppm	ASTM D5185m		956		
	Zinc	ppm	ASTM D5185m		995		
	Sulfur	ppm	ASTM D5185m		3232		
	Acid Number (AN)	mg KOH/g	ASTM D8045		0.91		

Visc @ 40°C cSt ASTM D445

Submitted By: RALEIGH SHOP







Laboratory Sample No. Lab Number Unique Number Test Package : CONST ( Additional Tests: PQ )

: 06054746

: JR0164588 : 10820695

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 Recieved Diagnosed

: 08 Jan 2024 : 10 Jan 2024 Diagnostician : Don Baldridge

4161 AUBURN CHURCH RD GARNER, NC US 27529

Contact: RALEIGH SHOP sean.betts@jamesriverequipment.com;catherine.anastasio@wearcheck.com T: (919)614-2260

To discuss this sample report, contact Customer Service at 1-800-237-1369. \* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012) F: (919)779-5432 Submitted By: RALEIGH SHOP

JRE - GARNER