



OIL ANALYSIS REPORT

WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL

Machine Id
KENWORTH 109
Component
Diesel Engine
Fluid
CHEVRON DELO 400 MULTIGRADE 15W40 (11 GAL)

RECOMMENDATION

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		WC0778895	WC0778885	WC0707334
Sample Date		Client Info		11 Sep 2023	11 May 2023	19 Oct 2022
Machine Age	hrs	Client Info		9791	9251	8578
Oil Age	hrs	Client Info		450	450	750
Filter Age	hrs	Client Info		450	450	750
Oil Changed		Client Info		Changed	Changed	Changed
Filter Changed		Client Info		Changed	Changed	Changed
Sample Status				NORMAL	NORMAL	NORMAL

WEAR

All component wear rates are normal.

Iron	ppm	ASTM D5185m	>90	8	90	31
Chromium	ppm	ASTM D5185m	>20	<1	5	2
Nickel	ppm	ASTM D5185m	>2	<1	0	0
Titanium	ppm	ASTM D5185m	>2	<1	<1	<1
Silver	ppm	ASTM D5185m	>2	0	0	0
Aluminum	ppm	ASTM D5185m	>20	3	29	3
Lead	ppm	ASTM D5185m	>40	<1	2	2
Copper	ppm	ASTM D5185m	>330	<1	2	1
Tin	ppm	ASTM D5185m	>15	<1	<1	<1
Vanadium	ppm	ASTM D5185m		0	<1	0
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE

CONTAMINATION











There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185m	>25	5	10	8
Potassium	ppm	ASTM D5185m	>20	7	62	6
Fuel		WC Method	>3.0	<1.0	<1.0	<1.0
Water		WC Method	>0.2	NEG	NEG	NEG
Glycol		WC Method		NEG	NEG	NEG
Soot %	%	*ASTM D7844	>6	0.3	2.3	1.4
Nitration	Abs/cm	*ASTM D7624	>20	6.0	12.9	12.4
Sulfation	Abs/.1mm	*ASTM D7415	>30	16.5	30.9	29.2
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG	NEG

FLUID CONDITION

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

Sodium	ppm	ASTM D5185m		3	4	3
Boron	ppm	ASTM D5185m		58	50	23
Barium	ppm	ASTM D5185m		0	0	0
Molybdenum	ppm	ASTM D5185m		49	10	3
Manganese	ppm	ASTM D5185m		<1	1	<1
Magnesium	ppm	ASTM D5185m		993	828	751
Calcium	ppm	ASTM D5185m		827	1647	1430
Phosphorus	ppm	ASTM D5185m	1360	865	811	732
Zinc	ppm	ASTM D5185m	1480	1114	986	899
Sulfur	ppm	ASTM D5185m		3530	3674	3559
Oxidation	Abs/.1mm	*ASTM D7414	>25	13.5	22.7	22.3
Base Number (BN)	mg KOH/g	ASTM D2896	12.2	10.35	7.89	6.07
Visc @ 100°C	cSt	ASTM D445	15.1	14.4	15.1	14.2



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : WC0778895 **Received** : 08 Jan 2024
Lab Number : 06055048 **Diagnosed** : 10 Jan 2024
Unique Number : 10820997 **Diagnostician** : Sean Felton
Test Package : MOB 2

LYNDEN TRANSPORT - FIFE
 5410 12TH STREET EAST
 FIFE, WA
 US 98424
 Contact: CHESTER ANGLEMYER
 chestera@ltia.lynden.com
 T: (253)926-7245
 F: (253)926-7249

To discuss this sample report, contact Customer Service at 1-800-237-1369.
 * - Denotes test methods that are outside of the ISO 17025 scope of accreditation.
 Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)