



OIL ANALYSIS REPORT

WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL

Machine Id
KENWORTH 763
Component
Diesel Engine
Fluid
CHEVRON DELO 400 MULTIGRADE 15W40 (24 QTS)

RECOMMENDATION

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		WC0844203	WC0778912	WC0707342
Sample Date		Client Info		08 Jan 2024	14 Jun 2023	28 Nov 2022
Machine Age	hrs	Client Info		10452	9772	9123
Oil Age	hrs	Client Info		450	450	450
Filter Age	hrs	Client Info		450	450	0
Oil Changed		Client Info		Changed	Changed	Changed
Filter Changed		Client Info		Changed	Changed	Changed
Sample Status				NORMAL	NORMAL	NORMAL

WEAR

All component wear rates are normal.

Iron	ppm	ASTM D5185m	>100	38	36	29
Chromium	ppm	ASTM D5185m	>20	1	1	1
Nickel	ppm	ASTM D5185m	>4	1	<1	<1
Titanium	ppm	ASTM D5185m		1	<1	<1
Silver	ppm	ASTM D5185m	>3	<1	<1	<1
Aluminum	ppm	ASTM D5185m	>20	4	8	7
Lead	ppm	ASTM D5185m	>40	4	3	5
Copper	ppm	ASTM D5185m	>330	4	4	2
Tin	ppm	ASTM D5185m	>15	1	<1	<1
Vanadium	ppm	ASTM D5185m		0	0	<1
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE

CONTAMINATION











There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185m	>25	9	8	6
Potassium	ppm	ASTM D5185m	>20	7	8	7
Fuel		WC Method	>5	<1.0	<1.0	<1.0
Water		WC Method	>0.2	NEG	NEG	NEG
Glycol		WC Method		NEG	NEG	NEG
Soot %	%	*ASTM D7844	>3	1	1	0.9
Nitration	Abs/cm	*ASTM D7624	>20	14.5	12.7	13.0
Sulfation	Abs/.1mm	*ASTM D7415	>30	27.3	25.8	27.4
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG	NEG

FLUID CONDITION

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

Sodium	ppm	ASTM D5185m		2	2	3
Boron	ppm	ASTM D5185m		28	31	30
Barium	ppm	ASTM D5185m		0	<1	0
Molybdenum	ppm	ASTM D5185m		6	7	12
Manganese	ppm	ASTM D5185m		1	<1	<1
Magnesium	ppm	ASTM D5185m		748	768	737
Calcium	ppm	ASTM D5185m		1400	1520	1439
Phosphorus	ppm	ASTM D5185m	1360	702	762	733
Zinc	ppm	ASTM D5185m	1480	865	923	883
Sulfur	ppm	ASTM D5185m		3565	3461	3522
Oxidation	Abs/.1mm	*ASTM D7414	>25	24.1	21.8	22.3
Base Number (BN)	mg KOH/g	ASTM D2896	12.2	5.82	5.62	5.52
Visc @ 100°C	cSt	ASTM D445	15.1	14.3	13.6	14.3



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : WC0844203 **Received** : 08 Jan 2024
Lab Number : 06055057 **Diagnosed** : 10 Jan 2024
Unique Number : 10821006 **Diagnostician** : Sean Felton
Test Package : MOB 2

LYNDEN TRANSPORT - FIFE
 5410 12TH STREET EAST
 FIFE, WA
 US 98424

Contact: CHESTER ANGLEMYER
 chestera@ltia.lynden.com
 T: (253)926-7245
 F: (253)926-7249

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)