



ASCENDUM

OIL ANALYSIS REPORT

WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL



Area
Ascendum Machinery
Machine Id
VOLVO L180H 14 (S/N 5269)
Component
Diesel Engine
Fluid
VOLVO VDS-4.5 Premium Motor Oil 15W40 (--- GAL)

RECOMMENDATION

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		ASC0000512	ASC0005171	ASC0005427
Sample Date		Client Info		29 Dec 2023	27 Nov 2023	26 Oct 2023
Machine Age	hrs	Client Info		14523	14071	13517
Oil Age	hrs	Client Info		1006	554	510
Filter Age	hrs	Client Info		554	554	510
Oil Changed		Client Info		Changed	Changed	Changed
Filter Changed		Client Info		Changed	Changed	Changed
Sample Status				NORMAL	NORMAL	NORMAL

WEAR

All component wear rates are normal.

Iron	ppm	ASTM D5185m	>100	3	3	<1
Chromium	ppm	ASTM D5185m	>10	<1	<1	0
Nickel	ppm	ASTM D5185m	>10	<1	<1	0
Titanium	ppm	ASTM D5185m		<1	<1	0
Silver	ppm	ASTM D5185m	>2	0	0	0
Aluminum	ppm	ASTM D5185m	>10	2	2	<1
Lead	ppm	ASTM D5185m	>20	<1	1	0
Copper	ppm	ASTM D5185m	>15	<1	1	0
Tin	ppm	ASTM D5185m	>10	<1	<1	<1
Vanadium	ppm	ASTM D5185m		0	0	0
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE

CONTAMINATION











There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185m	>20	4	4	4
Potassium	ppm	ASTM D5185m	>20	2	2	0
Fuel		WC Method	>6.0	<1.0	<1.0	<1.0
Water		WC Method	>0.1	NEG	NEG	NEG
Glycol		WC Method		NEG	NEG	NEG
Soot %	%	*ASTM D7844	>3	0.1	0.1	0.1
Nitration	Abs/cm	*ASTM D7624	>20	6.5	6.3	6.9
Sulfation	Abs/.1mm	*ASTM D7415	>30	22.5	21.5	21.8
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.1	NEG	NEG	NEG

FLUID CONDITION

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

Sodium	ppm	ASTM D5185m		0	0	<1
Boron	ppm	ASTM D5185m		47	43	37
Barium	ppm	ASTM D5185m		0	0	0
Molybdenum	ppm	ASTM D5185m		38	38	37
Manganese	ppm	ASTM D5185m		<1	<1	0
Magnesium	ppm	ASTM D5185m		494	487	502
Calcium	ppm	ASTM D5185m		1649	1638	1627
Phosphorus	ppm	ASTM D5185m		838	794	927
Zinc	ppm	ASTM D5185m		1094	1098	1137
Sulfur	ppm	ASTM D5185m		3217	2968	2890
Oxidation	Abs/.1mm	*ASTM D7414	>25	21.5	19.8	20.5
Base Number (BN)	mg KOH/g	ASTM D2896		10.0	10.1	10.3
Visc @ 100°C	cSt	ASTM D445		12.7	12.3	12.6



Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : ASC0000512 **Received** : 09 Jan 2024
Lab Number : 06055168 **Diagnosed** : 10 Jan 2024
Unique Number : 10821117 **Diagnostician** : Wes Davis
Test Package : MOBCE (Additional Tests: TBN)

EGGER WOOD PRODUCTS
 300 EGGER PARKWAY
 LINWOOD, NC
 US 27299
 Contact: HELMUT THOMAY
 helmut.thomay@egger.com
 T:
 F:

Certificate L2367
 To discuss this sample report, contact Customer Service at 1-800-237-1369.
 * - Denotes test methods that are outside of the ISO 17025 scope of accreditation.
 Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)