



OIL ANALYSIS REPORT

WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL

Machine Id
PETERBILT 117392
Component
Diesel Engine
Fluid
CHEVRON 15W40 (24 QTS)

RECOMMENDATION

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		RPL0009866	RPL0003403	RPL0003438
Sample Date		Client Info		27 Oct 2023	18 Nov 2022	04 Oct 2022
Machine Age	mls	Client Info		84097	49156	0
Oil Age	mls	Client Info		10640	6149	0
Filter Age	mls	Client Info		10640	6149	0
Oil Changed		Client Info		Changed	Changed	N/A
Filter Changed		Client Info		Changed	Changed	N/A
Sample Status				NORMAL	NORMAL	NORMAL

WEAR

All component wear rates are normal.

Iron	ppm	ASTM D5185m	>100	23	13	35
Chromium	ppm	ASTM D5185m	>20	2	1	3
Nickel	ppm	ASTM D5185m	>4	<1	<1	0
Titanium	ppm	ASTM D5185m		<1	0	0
Silver	ppm	ASTM D5185m	>3	0	<1	0
Aluminum	ppm	ASTM D5185m	>20	8	7	23
Lead	ppm	ASTM D5185m	>40	<1	1	0
Copper	ppm	ASTM D5185m	>330	1	<1	4
Tin	ppm	ASTM D5185m	>15	<1	<1	<1
Vanadium	ppm	ASTM D5185m		0	<1	0
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE

CONTAMINATION







Elevated aluminum (Al) and/or lead (Pb) and potassium (K) levels in your metals analysis are likely a result of solder flux release into the lubricant and is common on new equipment/components. There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185m	>25	9	11	15
Potassium	ppm	ASTM D5185m	>20	11	14	71
Fuel		WC Method	>5	<1.0	<1.0	<1.0
Water		WC Method	>0.2	NEG	NEG	NEG
Glycol		WC Method		NEG	NEG	NEG
Soot %	%	*ASTM D7844	>3	0.4	0.2	0.6
Nitration	Abs/cm	*ASTM D7624	>20	7.5	7.5	9.2
Sulfation	Abs/.1mm	*ASTM D7415	>30	21.1	21.0	24.5
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG	NEG

FLUID CONDITION

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

Sodium	ppm	ASTM D5185m	>50	0	3	2
Boron	ppm	ASTM D5185m		320	390	192
Barium	ppm	ASTM D5185m		0	0	0
Molybdenum	ppm	ASTM D5185m		82	82	84
Manganese	ppm	ASTM D5185m		1	<1	<1
Magnesium	ppm	ASTM D5185m		374	378	384
Calcium	ppm	ASTM D5185m		1371	1421	1414
Phosphorus	ppm	ASTM D5185m		910	1004	1020
Zinc	ppm	ASTM D5185m		1246	1278	1214
Sulfur	ppm	ASTM D5185m		3417	3470	3651
Oxidation	Abs/.1mm	*ASTM D7414	>25	15.0	15.2	18.1
Base Number (BN)	mg KOH/g	ASTM D2896		6.9	9.3	7.3
Visc @ 100°C	cSt	ASTM D445	14.4	12.8	12.8	12.8



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : RPL0009866 **Received** : 09 Jan 2024
Lab Number : 06055236 **Diagnosed** : 10 Jan 2024
Unique Number : 10821185 **Diagnostician** : Wes Davis
Test Package : FLEET

RTL PACLEASE - 7019 - Birmingham
 601 Republic Circle
 Birmingham, AL
 US 35214
 Contact: Johnathan King
 KingJ1@RushEnterprises.com

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

T:
F: