



WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL

Area
JOHN R INGRAM
Machine Id
[JOHN R INGRAM] 004 531157-4
Component
Port Reduction Gear
Fluid
CHEVRON MEROPA 320 (150 GAL)

RECOMMENDATION

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		MW06055504	MW0034239	MW0061565
Sample Date		Client Info		01 Dec 2023	01 Nov 2023	30 Sep 2023
Machine Age	hrs	Client Info		58224	57504	56736
Oil Age	hrs	Client Info		260	57504	56736
Filter Age	hrs	Client Info		0	0	56736
Oil Changed		Client Info		N/A	Not Changd	N/A
Filter Changed		Client Info		N/A	None	N/A
Sample Status				NORMAL	NORMAL	NORMAL

WEAR

All component wear rates are normal.

Iron	ppm	ASTM D5185m	>150	44	55	47
Chromium	ppm	ASTM D5185m	>10	4	4	5
Nickel	ppm	ASTM D5185m	>10	0	<1	1
Titanium	ppm	ASTM D5185m		0	0	<1
Silver	ppm	ASTM D5185m		0	0	0
Aluminum	ppm	ASTM D5185m	>25	4	5	4
Lead	ppm	ASTM D5185m	>100	<1	<1	2
Copper	ppm	ASTM D5185m	>50	5	5	5
Tin	ppm	ASTM D5185m	>10	0	0	<1
Vanadium	ppm	ASTM D5185m		0	0	0
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE

CONTAMINATION







There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185m	>50	4	6	6
Potassium	ppm	ASTM D5185m	>20	2	2	3
Water		WC Method	>0.1	NEG	NEG	NEG
Silt	scalar	*Visual	NONE	LIGHT	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.1	NEG	NEG	NEG

FLUID CONDITION

The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.

Sodium	ppm	ASTM D5185m		55	62	56
Boron	ppm	ASTM D5185m	20	10	12	11
Barium	ppm	ASTM D5185m		0	0	0
Molybdenum	ppm	ASTM D5185m	0	<1	5	3
Manganese	ppm	ASTM D5185m		0	<1	<1
Magnesium	ppm	ASTM D5185m		2	6	8
Calcium	ppm	ASTM D5185m	25	28	46	39
Phosphorus	ppm	ASTM D5185m	235	248	260	237
Zinc	ppm	ASTM D5185m		23	38	36
Sulfur	ppm	ASTM D5185m		5517	6087	6897
Acid Number (AN)	mg KOH/g	ASTM D8045	0.56	0.47	0.47	0.50
Visc @ 40°C	cSt	ASTM D445	304	323	323	323



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : MW06055504 **Recieved** : 09 Jan 2024
Lab Number : 06055504 **Diagnosed** : 10 Jan 2024
Unique Number : 10821453 **Diagnostician** : Wes Davis
Test Package : MAR 2

INGRAM BARGE
 900 S 3RD ST
 PADUCAH, KY
 US 42003
 Contact: GLENN ELLIS
 glen.ellis@ingrambarga.com
 T: (270)415-4467
 F: (615)695-3697

To discuss this sample report, contact Customer Service at 1-800-237-1369.
 * - Denotes test methods that are outside of the ISO 17025 scope of accreditation.
 Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)