
WEAR CONTAMINATION **FLUID CONDITION**

NORMAL NORMAL NORMAL

JIB KELB0116 590 J01 (S/N 329280)

Component Hoisting Gearbox

| RECOMMENDATION | Test | UOM | Method | Limit/Abn | Current | History1 | History2 |
|---|--------------------|---------------|----------------------------|-----------|-------------|----------|----------|
| Resample at the next service interval to monitor. Please specify the brand, type, and viscosity of the oil on your next sample. | Sample Number | | Client Info | | DC0033197 | | |
| | Sample Date | | Client Info | | 05 Jul 2023 | | |
| | Machine Age | hrs | Client Info | | 0 | | |
| | Oil Age | hrs | Client Info | | 0 | | |
| | Filter Age | hrs | Client Info | | 0 | | |
| | Oil Changed | | Client Info | | Not Changd | | |
| | Filter Changed | | Client Info | | Not Changd | | |
| | Sample Status | | | | NORMAL | | |
| A/E A D | | | | | | | |
| WEAR | Iron | ppm | ASTM D5185m | | 25 | | |
| All component wear rates are normal. | Chromium | ppm | ASTM D5185m | | 0 | | |
| | Nickel | ppm | ASTM D5185m | >10 | 0 | | |
| | Titanium Silver | ppm | ASTM D5185m | | 0 | | |
| | | ppm | ASTM D5185m | | 0 | | |
| | Aluminum | ppm | ASTM D5185m ASTM D5185m | | <1 0 | | |
| | Lead | ppm | ASTM D5185m | | 33 | | |
| | Tin | ppm | ASTM D5185m | | 0 | | |
| | Vanadium | ppm | ASTM D5185m | | 0 | | |
| | White Metal | ppm scalar | *Visual | NONE | NONE | | |
| | Yellow Metal | scalar | *Visual | NONE | NONE | | |
| ······ | | Scalai | visuai | | ····· | | |
| CONTAMINATION | Silicon | ppm | ASTM D5185m | | 4 | | |
| There is no indication of any contamination in the oil. | Potassium | ppm | ASTM D5185m | >20 | <1 | | |
| | Water | | WC Method | >0.2 | NEG | | |
| | Silt | scalar | *Visual | NONE | NONE | | |
| | Debris | scalar | *Visual | NONE | NONE | | |
| | Sand/Dirt | scalar | *Visual | NONE | NONE | | |
| | Appearance | scalar | *Visual | NORML | NORML | | |
| | Odor | scalar | *Visual | NORML | NORML | | |
| | Emulsified Water | scalar | *Visual | >0.2 | NEG | | |
| FLUID CONDITION | Sodium | ppm | ASTM D5185m | | 3 | | |
| The condition of the oil is acceptable for the time in service. | Boron | ppm | ASTM D5185m | | 143 | | |
| | Barium | ppm | ASTM D5185m | | 0 | | |
| | Molybdenum | ppm | ASTM D5185m | | 0 | | |
| | Manganese | ppm | ASTM D5185m | | 2 | | |
| | Magnesium | ppm | ASTM D5185m | | 4 | | |
| | Calcium | ppm | ASTM D5185m | | 354 | | |
| | Phosphorus | ppm | ASTM D5185m | | 433 | | |
| | Zinc | ppm | ASTM D5185m | | 122 | | |
| | Sulfur | ppm | ASTM D5185m | | 2346 | | |
| | | | | | | | |





Certificate L2367

Laboratory

Sample No. Lab Number **Unique Number**

: DC0033197 : 06055679 : 10821628 Test Package : MOB 1 To discuss this sample report, contact Customer Service at 1-800-237-1369.

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 Recieved : 09 Jan 2024

Diagnosed : 10 Jan 2024 : Jonathan Hester Diagnostician

CRANEWORKS INC - MID-ATLANTIC

11089 LEADBETTER ROAD ASHLAND, VA US 23005

Contact: JASON WILDE

jcwilde@vacraneworks.com T:

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation. Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

F: