



WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL

Machine Id
EPIROC D65-10 G22SED0578
 Component
Diesel Engine
 Fluid
DIESEL ENGINE OIL SAE 40 (--- GAL)

RECOMMENDATION

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		JR0197363	JR0163587	JR0181184
Sample Date		Client Info		08 Jan 2024	01 Dec 2023	17 Oct 2023
Machine Age	hrs	Client Info		2492	2255	1989
Oil Age	hrs	Client Info		2492	266	100
Filter Age	hrs	Client Info		0	266	100
Oil Changed		Client Info		Changed	Changed	Changed
Filter Changed		Client Info		Changed	Changed	Changed
Sample Status				NORMAL	ABNORMAL	NORMAL

WEAR

All component wear rates are normal.

Iron	ppm	ASTM D5185m	>100	8	13	11
Chromium	ppm	ASTM D5185m	>20	<1	<1	<1
Nickel	ppm	ASTM D5185m	>4	0	0	0
Titanium	ppm	ASTM D5185m		<1	0	0
Silver	ppm	ASTM D5185m	>3	0	0	0
Aluminum	ppm	ASTM D5185m	>20	3	4	4
Lead	ppm	ASTM D5185m	>40	0	0	2
Copper	ppm	ASTM D5185m	>330	3	5	5
Tin	ppm	ASTM D5185m	>15	<1	0	<1
Vanadium	ppm	ASTM D5185m		0	0	0
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE

CONTAMINATION







There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185m	>25	8	12	10
Potassium	ppm	ASTM D5185m	>20	3	4	<1
Fuel		WC Method	>5	<1.0	▲ 2.4	<1.0
Water		WC Method	>0.2	NEG	NEG	NEG
Glycol		WC Method		NEG	NEG	NEG
Soot %	%	*ASTM D7844	>3	0.2	0.2	0.3
Nitration	Abs/cm	*ASTM D7624	>20	8.4	8.5	9.1
Sulfation	Abs/.1mm	*ASTM D7415	>30	21.0	21.1	22.4
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG	NEG

FLUID CONDITION

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

Sodium	ppm	ASTM D5185m	>216	0	<1	2
Boron	ppm	ASTM D5185m	250	255	162	169
Barium	ppm	ASTM D5185m	10	0	3	0
Molybdenum	ppm	ASTM D5185m	100	188	213	258
Manganese	ppm	ASTM D5185m		0	0	<1
Magnesium	ppm	ASTM D5185m	450	662	833	809
Calcium	ppm	ASTM D5185m	3000	1247	▲ 2135	1448
Phosphorus	ppm	ASTM D5185m	1150	1097	1136	876
Zinc	ppm	ASTM D5185m	1350	927	▲ 1446	1064
Sulfur	ppm	ASTM D5185m	4250	5621	4517	3038
Oxidation	Abs/.1mm	*ASTM D7414	>25	16.4	17.5	17.5
Base Number (BN)	mg KOH/g	ASTM D2896	8.5	7.4	9.0	8.6
Visc @ 100°C	cSt	ASTM D445	14.4	12.8	▲ 12.4	12.8



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : JR0197363 **Received** : 09 Jan 2024
Lab Number : 06055719 **Diagnosed** : 10 Jan 2024
Unique Number : 10821668 **Diagnostician** : Jonathan Hester
Test Package : CONST (Additional Tests: TBN)

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

FUQUAY - MARTIN MARIETTA
 7400 BUCKHORN DUNCAN RD
 HOLLY SPRINGS, NC
 US 27549
 Contact: DARIN HESS
 darin.hess@martinmarietta.com

T:
F: