

## JOHN DEERE 350P 1FF350PAHPF000686

## Component Left Final Drive

## JOHN DEERE GL-5 80W90 (--- GAL)

RECOMMENDATION	Test	UOM	Method	Limit/Abn	Current	History1	History2
Resample at the next service interval to monitor.	Sample Number		Client Info		JR0199361		
	Sample Date		Client Info		08 Jan 2024		
	Machine Age	hrs	Client Info		500		
	Oil Age	hrs	Client Info		0		
	Filter Age	hrs	Client Info		0		
	Oil Changed		Client Info		Not Changd		
	Filter Changed		Client Info		Not Changd		
	Sample Status				NORMAL		
WEAR	PQ		ASTM D8184	> 1250	218		
WEAR	Iron	nnm	ASTM D5185m		276		
All component wear rates are normal.	Chromium	ppm	ASTM D5185m		5		
	Nickel	ppm	ASTM D5185m		0		
	Titanium	ppm	ASTM D5185m	>10	۰ <1		
	Silver	ppm	ASTM D5185m		0		
	Aluminum	ppm	ASTM D5185m	× 10	0 <1		
	Lead	ppm	ASTM D5185m		0		
	Copper	ppm	ASTM D5185m		۰ <1		
	Tin	ppm ppm	ASTM D5185m		0		
	Vanadium		ASTM D5185m	>10	۰ <1		
	White Metal	ppm scalar	*Visual	NONE	NONE		
	Yellow Metal	scalar	*Visual	NONE	NONE		
			v iSuai				
CONTAMINATION	Silicon	ppm	ASTM D5185m	>75	13		
There is no indication of any contamination in the oil.	Potassium	ppm	ASTM D5185m	>20	0		
	Water		WC Method	>0.075	NEG		
	Silt	scalar	*Visual	NONE	NONE		
	Debris	scalar	*Visual	NONE	LIGHT		
	Sand/Dirt	scalar	*Visual	NONE	NONE		
	Appearance	scalar	*Visual	NORML	NORML		
	Odor	scalar	*Visual	NORML	NORML		
	Emulsified Water	scalar	*Visual	>0.075	NEG		
FLUID CONDITION	Sodium	ppm	ASTM D5185m	>51	1		
	Boron	ppm	ASTM D5185m		69		
The condition of the oil is acceptable for the time in service.	Barium	ppm	ASTM D5185m		0		
	Molybdenum	ppm	ASTM D5185m		0		
	Manganese	ppm	ASTM D5185m		6		
	Magnesium	ppm	ASTM D5185m		0		
	Calcium	ppm	ASTM D5185m		24		
	Phosphorus	ppm	ASTM D5185m		532		
	Zinc	ppm	ASTM D5185m		5		
	Sulfur	ppm	ASTM D5185m		15148		


Visc @ 40°C


cSt

ASTM D445

Contact/Location: DANNY HUFF - BSSWAR

187





Contact/Location: DANNY HUFF - BSSWAR

Page 2 of 2