



OIL ANALYSIS REPORT

WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL

Machine Id
857-4730

Component
Diesel Engine

Fluid
MOBIL DELVAC 1300 SUPER 10W30 (--- GAL)

RECOMMENDATION

Resample at the next service interval to monitor. Please specify the component make and model with your next sample.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		RPL0010903	RPL0010145	RPL0004911
Sample Date		Client Info		22 Nov 2023	02 Jun 2023	29 Dec 2022
Machine Age	mls	Client Info		157971	122196	92933
Oil Age	mls	Client Info		35771	29263	27293
Filter Age	mls	Client Info		35771	29263	27293
Oil Changed		Client Info		Changed	Changed	Changed
Filter Changed		Client Info		Changed	Changed	Changed
Sample Status				NORMAL	NORMAL	NORMAL

WEAR

All component wear rates are normal.

Iron	ppm	ASTM D5185m	>100	63	45	78
Chromium	ppm	ASTM D5185m	>20	1	2	2
Nickel	ppm	ASTM D5185m	>4	0	0	0
Titanium	ppm	ASTM D5185m		0	0	0
Silver	ppm	ASTM D5185m	>3	0	<1	0
Aluminum	ppm	ASTM D5185m	>20	6	9	18
Lead	ppm	ASTM D5185m	>40	3	1	2
Copper	ppm	ASTM D5185m	>330	6	3	4
Tin	ppm	ASTM D5185m	>15	<1	1	1
Vanadium	ppm	ASTM D5185m		0	0	0
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE

CONTAMINATION







There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185m	>25	10	10	11
Potassium	ppm	ASTM D5185m	>20	20	21	54
Fuel		WC Method	>5	<1.0	<1.0	<1.0
Water		WC Method	>0.2	NEG	NEG	NEG
Glycol		WC Method		NEG	NEG	NEG
Soot %	%	*ASTM D7844	>3	1.8	1.4	1.2
Nitration	Abs/cm	*ASTM D7624	>20	13.4	11.9	12.3
Sulfation	Abs/.1mm	*ASTM D7415	>30	31.9	28.6	27.8
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG	NEG

FLUID CONDITION

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

Sodium	ppm	ASTM D5185m		4	3	3
Boron	ppm	ASTM D5185m		18	23	18
Barium	ppm	ASTM D5185m		0	0	0
Molybdenum	ppm	ASTM D5185m		15	12	20
Manganese	ppm	ASTM D5185m		0	1	2
Magnesium	ppm	ASTM D5185m		759	831	700
Calcium	ppm	ASTM D5185m		1441	1469	1449
Phosphorus	ppm	ASTM D5185m		758	760	711
Zinc	ppm	ASTM D5185m		875	913	894
Sulfur	ppm	ASTM D5185m		3076	3577	3019
Oxidation	Abs/.1mm	*ASTM D7414	>25	27.9	23.4	22.9
Base Number (BN)	mg KOH/g	ASTM D2896	10.5	4.4	5.6	5.5
Visc @ 100°C	cSt	ASTM D445	11.9	11.9	11.8	11.6



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : RPL0010903 **Received** : 10 Jan 2024
Lab Number : 06056213 **Diagnosed** : 11 Jan 2024
Unique Number : 10822162 **Diagnostician** : Angela Borella
Test Package : FLEET

RTL PACLEASE - 7001 - Houston
 6300 N. Loop East
 Houston, TX
 US 77026
 Contact: RODNEY BRIGGS
 briggs@rushenterprises.com

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

T:
F: