



WEAR	<b>NORMAL</b>
CONTAMINATION	<b>NORMAL</b>
FLUID CONDITION	<b>NORMAL</b>

Machine Id  
**JHA**  
Component  
**Starboard Genset**  
Fluid  
**CHEVRON DELO 710 LS (5 GAL)**

**RECOMMENDATION**

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		<b>MW0050593</b>	MW0050594	MW0050589
Sample Date		Client Info		<b>09 Nov 2023</b>	17 Oct 2023	23 Sep 2023
Machine Age	hrs	Client Info		<b>16602</b>	16304	16016
Oil Age	hrs	Client Info		<b>300</b>	288	304
Filter Age	hrs	Client Info		<b>300</b>	288	304
Oil Changed		Client Info		<b>Changed</b>	Changed	Changed
Filter Changed		Client Info		<b>Changed</b>	Changed	Changed
Sample Status				<b>NORMAL</b>	NORMAL	NORMAL

**WEAR**

All component wear rates are normal.

Iron	ppm	ASTM D5185m	>50	<b>&lt;1</b>	4	3
Chromium	ppm	ASTM D5185m	>4	<b>0</b>	<1	0
Nickel	ppm	ASTM D5185m	>2	<b>0</b>	0	0
Titanium	ppm	ASTM D5185m		<b>0</b>	<1	0
Silver	ppm	ASTM D5185m	>5	<b>0</b>	0	0
Aluminum	ppm	ASTM D5185m	>12	<b>1</b>	2	<1
Lead	ppm	ASTM D5185m	>17	<b>0</b>	<1	0
Copper	ppm	ASTM D5185m	>70	<b>0</b>	1	0
Tin	ppm	ASTM D5185m	>15	<b>&lt;1</b>	<1	0
Vanadium	ppm	ASTM D5185m		<b>0</b>	<1	0
White Metal	scalar	*Visual	NONE	<b>NONE</b>	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	<b>NONE</b>	NONE	NONE

**CONTAMINATION**







There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185m	>25	<b>3</b>	3	2
Potassium	ppm	ASTM D5185m	>20	<b>1</b>	2	1
Fuel		WC Method	>4.0	<b>&lt;1.0</b>	<1.0	<1.0
Water		WC Method	>0.1	<b>NEG</b>	NEG	NEG
Glycol		WC Method		<b>NEG</b>	NEG	NEG
Soot %	%	*ASTM D7844		<b>0</b>	0.1	0.1
Nitration	Abs/cm	*ASTM D7624	>20	<b>5.1</b>	7.0	6.2
Sulfation	Abs/.1mm	*ASTM D7415	>30	<b>13.0</b>	14.4	13.4
Silt	scalar	*Visual	NONE	<b>NONE</b>	NONE	NONE
Debris	scalar	*Visual	NONE	<b>NONE</b>	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	<b>NONE</b>	NONE	NONE
Appearance	scalar	*Visual	NORML	<b>NORML</b>	NORML	NORML
Odor	scalar	*Visual	NORML	<b>NORML</b>	NORML	NORML
Emulsified Water	scalar	*Visual	>0.1	<b>NEG</b>	NEG	NEG

**FLUID CONDITION**

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

Sodium	ppm	ASTM D5185m		<b>0</b>	2	<1
Boron	ppm	ASTM D5185m		<b>40</b>	42	38
Barium	ppm	ASTM D5185m		<b>0</b>	0	0
Molybdenum	ppm	ASTM D5185m		<b>39</b>	41	42
Manganese	ppm	ASTM D5185m		<b>&lt;1</b>	<1	0
Magnesium	ppm	ASTM D5185m		<b>9</b>	0	12
Calcium	ppm	ASTM D5185m		<b>3194</b>	3113	3072
Phosphorus	ppm	ASTM D5185m		<b>4</b>	0	1
Zinc	ppm	ASTM D5185m		<b>0</b>	0	0
Sulfur	ppm	ASTM D5185m		<b>2124</b>	1731	1996
Oxidation	Abs/.1mm	*ASTM D7414	>25	<b>6.4</b>	8.6	7.1
Base Number (BN)	mg KOH/g	ASTM D2896	10.5	<b>6.0</b>	6.0	5.6
Visc @ 100°C	cSt	ASTM D445	15.5	<b>14.7</b>	14.1	14.3



Certificate L2367

**Laboratory** : WearCheck USA - 501 Madison Ave., Cary, NC 27513  
**Sample No.** : MW0050593 **Received** : 10 Jan 2024  
**Lab Number** : 06056326 **Diagnosed** : 11 Jan 2024  
**Unique Number** : 10822275 **Diagnostician** : Wes Davis  
**Test Package** : MAR 2

**AMERICAN RIVER TRANSPORTATION CO.**  
P.O. BOX 2889  
ST. LOUIS, MO  
US 63111  
Contact: BRIAN GRIEWING  
brian.griewing@adm.com  
T:  
F: (314)481-5278

To discuss this sample report, contact Customer Service at 1-800-237-1369.

\* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)