



WEAR	<b>NORMAL</b>
CONTAMINATION	<b>NORMAL</b>
FLUID CONDITION	<b>NORMAL</b>

Machine Id  
**744001**  
 Component  
**Natural Gas Engine**  
 Fluid  
**PETRO CANADA DURON GEO LD 15W40 (--- LTR)**

**RECOMMENDATION**

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		<b>GFL0106981</b>	GFL0094263	GFL0085406
Sample Date		Client Info		<b>06 Jan 2024</b>	03 Oct 2023	23 Jun 2023
Machine Age	hrs	Client Info		<b>23655</b>	24517	23910
Oil Age	hrs	Client Info		<b>0</b>	607	242
Filter Age	hrs	Client Info		<b>0</b>	607	242
Oil Changed		Client Info		<b>N/A</b>	Changed	Changed
Filter Changed		Client Info		<b>N/A</b>	Changed	Changed
Sample Status				<b>NORMAL</b>	NORMAL	NORMAL

**WEAR**

All component wear rates are normal.

Iron	ppm	ASTM D5185m	>50	<b>19</b>	6	4
Chromium	ppm	ASTM D5185m	>4	<b>&lt;1</b>	<1	0
Nickel	ppm	ASTM D5185m	>2	<b>0</b>	<1	0
Titanium	ppm	ASTM D5185m		<b>0</b>	0	0
Silver	ppm	ASTM D5185m	>3	<b>0</b>	0	0
Aluminum	ppm	ASTM D5185m	>9	<b>&lt;1</b>	3	0
Lead	ppm	ASTM D5185m	>30	<b>0</b>	<1	<1
Copper	ppm	ASTM D5185m	>35	<b>0</b>	<1	<1
Tin	ppm	ASTM D5185m	>4	<b>&lt;1</b>	0	0
Vanadium	ppm	ASTM D5185m		<b>0</b>	0	0
White Metal	scalar	*Visual	NONE	<b>NONE</b>	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	<b>NONE</b>	NONE	NONE

**CONTAMINATION**







There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185m	>+100	<b>3</b>	3	2
Potassium	ppm	ASTM D5185m	>20	<b>8</b>	4	2
Water		WC Method	>0.1	<b>NEG</b>	NEG	NEG
Soot %	%	*ASTM D7844		<b>1.5</b>	0	0.1
Nitration	Abs/cm	*ASTM D7624	>20	<b>10.0</b>	9.5	8.0
Sulfation	Abs/.1mm	*ASTM D7415	>30	<b>20.7</b>	19.6	19.5
Silt	scalar	*Visual	NONE	<b>NONE</b>	NONE	NONE
Debris	scalar	*Visual	NONE	<b>NONE</b>	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	<b>NONE</b>	NONE	NONE
Appearance	scalar	*Visual	NORML	<b>NORML</b>	NORML	NORML
Odor	scalar	*Visual	NORML	<b>NORML</b>	NORML	NORML
Emulsified Water	scalar	*Visual	>0.1	<b>NEG</b>	NEG	NEG

**FLUID CONDITION**

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

Sodium	ppm	ASTM D5185m		<b>15</b>	6	1
Boron	ppm	ASTM D5185m	50	<b>3</b>	15	25
Barium	ppm	ASTM D5185m	5	<b>0</b>	0	0
Molybdenum	ppm	ASTM D5185m	50	<b>57</b>	54	51
Manganese	ppm	ASTM D5185m	0	<b>&lt;1</b>	<1	<1
Magnesium	ppm	ASTM D5185m	560	<b>865</b>	572	526
Calcium	ppm	ASTM D5185m	1510	<b>1041</b>	1502	1512
Phosphorus	ppm	ASTM D5185m	780	<b>1050</b>	741	765
Zinc	ppm	ASTM D5185m	870	<b>1244</b>	974	923
Sulfur	ppm	ASTM D5185m	2040	<b>2970</b>	2755	2386
Oxidation	Abs/.1mm	*ASTM D7414	>25	<b>16.5</b>	17.1	17.4
Base Number (BN)	mg KOH/g	ASTM D2896	10.2	<b>8.6</b>	5.6	7.4
Visc @ 100°C	cSt	ASTM D445	15.1	<b>12.7</b>	14.7	14.9



Certificate L2367

**Laboratory** : WearCheck USA - 501 Madison Ave., Cary, NC 27513  
**Sample No.** : GFL0106981 **Received** : 10 Jan 2024  
**Lab Number** : 06056370 **Diagnosed** : 11 Jan 2024  
**Unique Number** : 10822319 **Diagnostician** : Jonathan Hester  
**Test Package** : FLEET

**GFL Environmental - 882 - Gainesville**  
 5002 SW 41st Blvd  
 Gainesville, FL  
 US 32608  
 Contact: ROBERT CLARK  
 robert.clark@gflenv.com

To discuss this sample report, contact Customer Service at 1-800-237-1369.

\* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

T:  
F: