



WEAR	ABNORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL



Machine Id
JOHN DEERE 300G 1FF300GXCNF732173

Component
Diesel Engine

Fluid
JOHN DEERE ENGINE OIL PLUS 50 II 15W40 (22 QTS)

RECOMMENDATION

Oil and filter change at the time of sampling has been noted. No corrective action is recommended at this time. Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		JR0192980	JR0172705	---
Sample Date		Client Info		30 Nov 2023	29 Jun 2023	---
Machine Age	hrs	Client Info		961	513	---
Oil Age	hrs	Client Info		500	513	---
Filter Age	hrs	Client Info		500	513	---
Oil Changed		Client Info		Changed	Changed	---
Filter Changed		Client Info		Changed	Changed	---
Sample Status				ABNORMAL	ABNORMAL	---

WEAR

The copper level is abnormal. In the absence of other significant wear metals, suspect copper due to sources other than wear (i.e. cooling core). All other component wear rates are normal.

Iron	ppm	ASTM D5185m	>51	31	44	---
Chromium	ppm	ASTM D5185m	>11	<1	1	---
Nickel	ppm	ASTM D5185m	>5	17	4	---
Titanium	ppm	ASTM D5185m		<1	<1	---
Silver	ppm	ASTM D5185m	>3	0	0	---
Aluminum	ppm	ASTM D5185m	>31	2	1	---
Lead	ppm	ASTM D5185m	>26	4	<1	---
Copper	ppm	ASTM D5185m	>26	▲ 356	▲ 375	---
Tin	ppm	ASTM D5185m	>4	1	2	---
Vanadium	ppm	ASTM D5185m		<1	0	---
White Metal	scalar	*Visual	NONE	NONE	NONE	---
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	---

CONTAMINATION








There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185m	>22	10	14	---
Potassium	ppm	ASTM D5185m	>20	5	2	---
Fuel		WC Method	>2.1	<1.0	0.4	---
Water		WC Method	>0.21	NEG	NEG	---
Glycol		WC Method		NEG	NEG	---
Soot %	%	*ASTM D7844	>3	0.4	0.4	---
Nitration	Abs/cm	*ASTM D7624	>20	9.0	9.1	---
Sulfation	Abs/.1mm	*ASTM D7415	>30	22.2	24.1	---
Silt	scalar	*Visual	NONE	NONE	NONE	---
Debris	scalar	*Visual	NONE	NONE	NONE	---
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	---
Appearance	scalar	*Visual	NORML	NORML	NORML	---
Odor	scalar	*Visual	NORML	NORML	NORML	---
Emulsified Water	scalar	*Visual	>0.21	NEG	NEG	---

FLUID CONDITION

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

Sodium	ppm	ASTM D5185m	>31	3	5	---
Boron	ppm	ASTM D5185m		189	201	---
Barium	ppm	ASTM D5185m		<1	0	---
Molybdenum	ppm	ASTM D5185m		232	258	---
Manganese	ppm	ASTM D5185m		3	8	---
Magnesium	ppm	ASTM D5185m		744	820	---
Calcium	ppm	ASTM D5185m		1417	1483	---
Phosphorus	ppm	ASTM D5185m		879	844	---
Zinc	ppm	ASTM D5185m		1031	1009	---
Sulfur	ppm	ASTM D5185m		2690	3107	---
Oxidation	Abs/.1mm	*ASTM D7414	>25	17.7	20.7	---
Base Number (BN)	mg KOH/g	ASTM D2896	13.6	8.0	8.3	---
Visc @ 100°C	cSt	ASTM D445	15.4	13.4	▲ 10.4	---



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : JR0192980 **Received** : 10 Jan 2024
Lab Number : 06056540 **Diagnosed** : 11 Jan 2024
Unique Number : 10822489 **Diagnostician** : Don Baldrige
Test Package : CONST (Additional Tests: TBN)

JRE - CHARLOTTE
 9550 STATESVILLE ROAD
 CHARLOTTE, NC
 US 28269

Contact: CHARLOTTE SHOP
 myoung@jamesriverequipment.com

T: (704)597-0211
 F: (704)596-6198

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)