



OIL ANALYSIS REPORT

WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL

Machine Id
DURALENE DT5B 5W30

Component
New (Unused) Oil

Fluid
{not provided} (--- LTR)

RECOMMENDATION

This is a baseline read-out on the submitted sample.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		DC0031132	DC0031347	DC0031337
Sample Date		Client Info		22 Dec 2023	13 Nov 2023	26 Oct 2023
Machine Age	mls	Client Info		0	0	0
Oil Age	mls	Client Info		0	0	0
Filter Age	mls	Client Info		0	0	0
Oil Changed		Client Info		N/A	N/A	N/A
Filter Changed		Client Info		N/A	N/A	N/A
Sample Status				NORMAL	NORMAL	NORMAL

WEAR









Iron	ppm	ASTM D5185m		0	0	0
Chromium	ppm	ASTM D5185m		<1	0	0
Nickel	ppm	ASTM D5185m		<1	<1	0
Titanium	ppm	ASTM D5185m		<1	0	0
Silver	ppm	ASTM D5185m		<1	0	0
Aluminum	ppm	ASTM D5185m		2	2	<1
Lead	ppm	ASTM D5185m		2	0	0
Copper	ppm	ASTM D5185m		<1	1	0
Tin	ppm	ASTM D5185m		2	0	0
Vanadium	ppm	ASTM D5185m		<1	<1	0
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE

CONTAMINATION

Silicon	ppm	ASTM D5185m		8	7	7
Potassium	ppm	ASTM D5185m	>20	3	<1	2
Water		WC Method		NEG	NEG	NEG
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual		NEG	NEG	NEG

FLUID CONDITION

Sodium	ppm	ASTM D5185m		0	<1	0
Boron	ppm	ASTM D5185m		127	136	158
Barium	ppm	ASTM D5185m		0	0	0
Molybdenum	ppm	ASTM D5185m		39	38	33
Manganese	ppm	ASTM D5185m		<1	<1	0
Magnesium	ppm	ASTM D5185m		695	692	613
Calcium	ppm	ASTM D5185m		686	723	680
Phosphorus	ppm	ASTM D5185m		590	597	475
Zinc	ppm	ASTM D5185m		687	706	594
Sulfur	ppm	ASTM D5185m		2316	2354	2055
Acid Number (AN)	mg KOH/g	ASTM D8045		1.47	1.50	1.51
Base Number (BN)	mg KOH/g	ASTM D2896		7.33	7.25	9.53
Visc @ 40°C	cSt	ASTM D445		61.74	68.25	63.98
Visc @ 100°C	cSt	ASTM D445		10.41	11.38	10.65
Viscosity Index (VI)	Scale	ASTM D2270		157	160	156



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : DC0031132 **Received** : 10 Jan 2024
Lab Number : 06057107 **Diagnosed** : 12 Jan 2024
Unique Number : 10823056 **Diagnostician** : Jonathan Hester
Test Package : MOB 2 (Additional Tests: FT-IR, ICP-NewOil, KV100, PrtCount, TBN, etc.)

THE UNITED OIL COMPANY - OPERATIONS
 4405 E. BALTIMORE ST
 BALTIMORE, MD
 US 21224
 Contact: MICHELLE HORNING

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

T:
 F: (410)327-7695