



WEAR	<b>NORMAL</b>
CONTAMINATION	<b>NORMAL</b>
FLUID CONDITION	<b>NORMAL</b>



Area  
**MONTGOMERY**  
Machine Id  
**MACK 920016-192537**  
Component  
**Diesel Engine**  
Fluid  
**PETRO CANADA DURON SHP 15W40 (--- LTR)**

**RECOMMENDATION**

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		<b>GFL0081885</b>	GFL0091289	GFL0089869
Sample Date		Client Info		<b>02 Jan 2024</b>	24 Nov 2023	19 Oct 2023
Machine Age	hrs	Client Info		<b>11097</b>	10809	10533
Oil Age	hrs	Client Info		<b>288</b>	525	249
Filter Age	hrs	Client Info		<b>0</b>	0	0
Oil Changed		Client Info		<b>Changed</b>	Changed	N/A
Filter Changed		Client Info		<b>Changed</b>	Changed	N/A
Sample Status				<b>NORMAL</b>	NORMAL	NORMAL

**WEAR**

All component wear rates are normal.

Iron	ppm	ASTM D5185m	>120	<b>9</b>	13	4
Chromium	ppm	ASTM D5185m	>20	<b>&lt;1</b>	<1	<1
Nickel	ppm	ASTM D5185m	>5	<b>0</b>	<1	<1
Titanium	ppm	ASTM D5185m	>2	<b>0</b>	<1	<1
Silver	ppm	ASTM D5185m	>2	<b>0</b>	0	0
Aluminum	ppm	ASTM D5185m	>20	<b>2</b>	<1	1
Lead	ppm	ASTM D5185m	>40	<b>0</b>	<1	0
Copper	ppm	ASTM D5185m	>330	<b>1</b>	3	<1
Tin	ppm	ASTM D5185m	>15	<b>0</b>	<1	<1
Vanadium	ppm	ASTM D5185m		<b>0</b>	0	0
White Metal	scalar	*Visual	NONE	<b>NONE</b>	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	<b>NONE</b>	NONE	NONE

**CONTAMINATION**







There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185m	>25	<b>3</b>	6	4
Potassium	ppm	ASTM D5185m	>20	<b>2</b>	3	3
Fuel		WC Method	>3.0	<b>&lt;1.0</b>	<1.0	<1.0
Water		WC Method	>0.2	<b>NEG</b>	NEG	NEG
Glycol		WC Method		<b>NEG</b>	NEG	NEG
Soot %	%	*ASTM D7844	>4	<b>0.6</b>	1	0.4
Nitration	Abs/cm	*ASTM D7624	>20	<b>7.1</b>	8.2	6.1
Sulfation	Abs/.1mm	*ASTM D7415	>30	<b>18.4</b>	18.8	17.3
Silt	scalar	*Visual	NONE	<b>NONE</b>	NONE	NONE
Debris	scalar	*Visual	NONE	<b>NONE</b>	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	<b>NONE</b>	NONE	NONE
Appearance	scalar	*Visual	NORML	<b>NORML</b>	NORML	NORML
Odor	scalar	*Visual	NORML	<b>NORML</b>	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	<b>NEG</b>	NEG	NEG

**FLUID CONDITION**

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

Sodium	ppm	ASTM D5185m		<b>2</b>	3	3
Boron	ppm	ASTM D5185m	0	<b>2</b>	2	2
Barium	ppm	ASTM D5185m	0	<b>0</b>	<1	0
Molybdenum	ppm	ASTM D5185m	60	<b>62</b>	63	53
Manganese	ppm	ASTM D5185m	0	<b>0</b>	<1	<1
Magnesium	ppm	ASTM D5185m	1010	<b>976</b>	944	911
Calcium	ppm	ASTM D5185m	1070	<b>1072</b>	1078	956
Phosphorus	ppm	ASTM D5185m	1150	<b>1030</b>	970	876
Zinc	ppm	ASTM D5185m	1270	<b>1254</b>	1181	1154
Sulfur	ppm	ASTM D5185m	2060	<b>3264</b>	3212	2747
Oxidation	Abs/.1mm	*ASTM D7414	>25	<b>13.5</b>	14.0	12.9
Base Number (BN)	mg KOH/g	ASTM D2896	9.8	<b>8.4</b>	7.5	8.2
Visc @ 100°C	cSt	ASTM D445	15.4	<b>13.6</b>	13.6	13.6



Certificate L2367

**Laboratory** : WearCheck USA - 501 Madison Ave., Cary, NC 27513  
**Sample No.** : GFL0081885 **Received** : 10 Jan 2024  
**Lab Number** : 06057294 **Diagnosed** : 11 Jan 2024  
**Unique Number** : 10823243 **Diagnostician** : Wes Davis  
**Test Package** : FLEET

**GFL Environmental - 955 - Montgomery**  
 1121 Wilbanks St  
 Montgomery, AL  
 US 36108  
 Contact: LISA REEVES

To discuss this sample report, contact Customer Service at 1-800-237-1369.  
 \* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.  
 Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

T:  
F: