

Area
KEMP QUARRIES / KEMP STONE - FAIRLAND

Machine Id
OHT123

Component
Diesel Engine

Fluid
PETRO CANADA DURON SHP 15W40 (--- GAL)

RECOMMENDATION

Resample at the next service interval to monitor. (Customer Sample
Comment: PM-1 changed filters and fluid)

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		PCA0070631	PCA0084732	PCA0086314
Sample Date		Client Info		02 Jan 2024	02 Oct 2023	21 Jun 2023
Machine Age	hrs	Client Info		37987	37517	37279
Oil Age	hrs	Client Info		37987	37517	37279
Filter Age	hrs	Client Info		0	0	0
Oil Changed		Client Info		Changed	Changed	Changed
Filter Changed		Client Info		Changed	Changed	Changed
Sample Status				NORMAL	NORMAL	NORMAL

WEAR

All component wear rates are normal.

Iron	ppm	ASTM D5185m	>100	41	28	64
Chromium	ppm	ASTM D5185m	>20	<1	<1	2
Nickel	ppm	ASTM D5185m	>4	0	<1	1
Titanium	ppm	ASTM D5185m		0	<1	0
Silver	ppm	ASTM D5185m	>3	0	0	0
Aluminum	ppm	ASTM D5185m	>20	2	2	<1
Lead	ppm	ASTM D5185m	>40	2	3	9
Copper	ppm	ASTM D5185m	>330	5	5	9
Tin	ppm	ASTM D5185m	>15	0	<1	2
Vanadium	ppm	ASTM D5185m		0	<1	0
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE

CONTAMINATION











There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185m	>25	4	3	5
Potassium	ppm	ASTM D5185m	>20	1	1	2
Fuel		WC Method	>5	<1.0	<1.0	<1.0
Water		WC Method	>0.2	NEG	NEG	NEG
Glycol		WC Method		NEG	NEG	NEG
Soot %	%	*ASTM D7844	>3	0.6	0.5	0.3
Nitration	Abs/cm	*ASTM D7624	>20	11.3	9.7	7.5
Sulfation	Abs/.1mm	*ASTM D7415	>30	22.9	20.9	18.5
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG	NEG

FLUID CONDITION

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

Sodium	ppm	ASTM D5185m		2	4	8
Boron	ppm	ASTM D5185m	0	0	0	4
Barium	ppm	ASTM D5185m	0	0	4	0
Molybdenum	ppm	ASTM D5185m	60	67	59	66
Manganese	ppm	ASTM D5185m	0	0	<1	<1
Magnesium	ppm	ASTM D5185m	1010	1052	882	942
Calcium	ppm	ASTM D5185m	1070	1138	1031	1277
Phosphorus	ppm	ASTM D5185m	1150	1097	971	1038
Zinc	ppm	ASTM D5185m	1270	1341	1153	1304
Sulfur	ppm	ASTM D5185m	2060	3431	2722	3105
Oxidation	Abs/.1mm	*ASTM D7414	>25	23.1	18.7	10.7
Base Number (BN)	mg KOH/g	ASTM D2896	9.8	7.7	8.3	7.0
Visc @ 100°C	cSt	ASTM D445	15.4	14.4	14.4	14.6



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : PCA0070631 **Received** : 10 Jan 2024
Lab Number : 06057299 **Diagnosed** : 12 Jan 2024
Unique Number : 10823248 **Diagnostician** : Sean Felton
Test Package : MOB 1 (Additional Tests: TBN)

Kemp Quarries - Kemp Stone - Fairland
 18350 S 590 Rd
 Fairland, OK
 US 74343
 Contact:
 fairland@kempstone.com

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

T:
F: