



OIL ANALYSIS REPORT

WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL

Machine Id
DEISTER 14051
Component
Lower Bearing
Fluid
MOBIL SHC 632 (4 GAL)

RECOMMENDATION

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		WC0749215	WC0749210	WC0441133
Sample Date		Client Info		21 Dec 2023	19 Apr 2023	22 Jan 2021
Machine Age	hrs	Client Info		0	0	0
Oil Age	hrs	Client Info		528	1813	2369
Filter Age	hrs	Client Info		0	0	0
Oil Changed		Client Info		Not Changd	N/A	Changed
Filter Changed		Client Info		N/A	N/A	N/A
Sample Status				NORMAL	ABNORMAL	NORMAL

WEAR

All component wear rates are normal.

Iron	ppm	ASTM D5185m	>200	30	120	42
Chromium	ppm	ASTM D5185m	>5	0	<1	<1
Nickel	ppm	ASTM D5185m	>5	0	0	0
Titanium	ppm	ASTM D5185m	>5	0	0	0
Silver	ppm	ASTM D5185m		0	0	0
Aluminum	ppm	ASTM D5185m	>25	0	1	0
Lead	ppm	ASTM D5185m	>50	2	0	4
Copper	ppm	ASTM D5185m	>150	7	24	24
Tin	ppm	ASTM D5185m	>10	1	2	2
Vanadium	ppm	ASTM D5185m		0	0	0
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE

CONTAMINATION










There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185m	>25	11	16	5
Potassium	ppm	ASTM D5185m	>20	1	<1	0
Water		WC Method	>0.1	NEG	NEG	NEG
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	LIGHT	▲ MODER	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.1	NEG	NEG	NEG

FLUID CONDITION

The condition of the oil is acceptable for the time in service.

Sodium	ppm	ASTM D5185m		0	1	0
Boron	ppm	ASTM D5185m		0	0	0
Barium	ppm	ASTM D5185m		0	0	0
Molybdenum	ppm	ASTM D5185m		0	0	0
Manganese	ppm	ASTM D5185m		<1	2	<1
Magnesium	ppm	ASTM D5185m		0	1	0
Calcium	ppm	ASTM D5185m		0	2	<1
Phosphorus	ppm	ASTM D5185m		425	430	324
Zinc	ppm	ASTM D5185m		0	3	0
Sulfur	ppm	ASTM D5185m		27	425	213
Visc @ 40°C	cSt	ASTM D445	325.8	341	328	332



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : WC0749215 **Received** : 10 Jan 2024
Lab Number : 06057525 **Diagnosed** : 12 Jan 2024
Unique Number : 10823474 **Diagnostician** : Sean Felton
Test Package : MOB 1

WAKE STONE CORPORATION-CARY
 222 STAR LANE
 CARY, NC
 US 27591
 Contact: PAUL PIERCE
 paulpierce@wakestonecorp.com
 T: (919)677-0050
 F: (919)677-0988

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)