



WEAR	<b>NORMAL</b>
CONTAMINATION	<b>NORMAL</b>
FLUID CONDITION	<b>NORMAL</b>

Machine Id  
**3841C AUTOCAR ACX**  
 Component  
**Natural Gas Engine**  
 Fluid  
**PETRO CANADA DURON GEO LD 15W40 (48 QTS)**

**RECOMMENDATION**

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		<b>GFL0103224</b>	GFL0089324	GFL0087136
Sample Date		Client Info		<b>09 Jan 2024</b>	08 Aug 2023	19 Jul 2023
Machine Age	hrs	Client Info		<b>13682</b>	12475	12301
Oil Age	hrs	Client Info		<b>1207</b>	174	3484
Filter Age	hrs	Client Info		<b>0</b>	0	0
Oil Changed		Client Info		<b>Changed</b>	Changed	Changed
Filter Changed		Client Info		<b>N/A</b>	Changed	Changed
Sample Status				<b>NORMAL</b>	NORMAL	NORMAL

**WEAR**

All component wear rates are normal.

Iron	ppm	ASTM D5185m	>50	<b>8</b>	8	9
Chromium	ppm	ASTM D5185m	>4	<b>&lt;1</b>	<1	<1
Nickel	ppm	ASTM D5185m	>2	<b>0</b>	0	0
Titanium	ppm	ASTM D5185m		<b>0</b>	<1	<1
Silver	ppm	ASTM D5185m	>3	<b>0</b>	0	0
Aluminum	ppm	ASTM D5185m	>9	<b>1</b>	2	3
Lead	ppm	ASTM D5185m	>30	<b>19</b>	9	4
Copper	ppm	ASTM D5185m	>35	<b>4</b>	3	6
Tin	ppm	ASTM D5185m	>4	<b>0</b>	<1	0
Vanadium	ppm	ASTM D5185m		<b>0</b>	<1	0
White Metal	scalar	*Visual	NONE	<b>NONE</b>	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	<b>NONE</b>	NONE	NONE

**CONTAMINATION**







There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185m	>+100	<b>6</b>	6	9
Potassium	ppm	ASTM D5185m	>20	<b>&lt;1</b>	<1	0
Water		WC Method	>0.1	<b>NEG</b>	NEG	NEG
Soot %	%	*ASTM D7844		<b>0</b>	0	0
Nitration	Abs/cm	*ASTM D7624	>20	<b>12.3</b>	11.3	11.4
Sulfation	Abs/.1mm	*ASTM D7415	>30	<b>26.8</b>	24.1	23.9
Silt	scalar	*Visual	NONE	<b>NONE</b>	NONE	NONE
Debris	scalar	*Visual	NONE	<b>NONE</b>	NONE	MODER
Sand/Dirt	scalar	*Visual	NONE	<b>NONE</b>	NONE	NONE
Appearance	scalar	*Visual	NORML	<b>NORML</b>	NORML	NORML
Odor	scalar	*Visual	NORML	<b>NORML</b>	NORML	NORML
Emulsified Water	scalar	*Visual	>0.1	<b>NEG</b>	NEG	NEG

**FLUID CONDITION**

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

Sodium	ppm	ASTM D5185m		<b>7</b>	6	7
Boron	ppm	ASTM D5185m	50	<b>13</b>	8	11
Barium	ppm	ASTM D5185m	5	<b>0</b>	0	0
Molybdenum	ppm	ASTM D5185m	50	<b>52</b>	53	56
Manganese	ppm	ASTM D5185m	0	<b>0</b>	<1	<1
Magnesium	ppm	ASTM D5185m	560	<b>617</b>	589	617
Calcium	ppm	ASTM D5185m	1510	<b>1691</b>	1760	1831
Phosphorus	ppm	ASTM D5185m	780	<b>771</b>	729	782
Zinc	ppm	ASTM D5185m	870	<b>1083</b>	1022	1059
Sulfur	ppm	ASTM D5185m	2040	<b>2259</b>	2827	3043
Oxidation	Abs/.1mm	*ASTM D7414	>25	<b>23.8</b>	21.6	20.9
Base Number (BN)	mg KOH/g	ASTM D2896	10.2	<b>3.7</b>	3.6	4.3
Visc @ 100°C	cSt	ASTM D445	15.1	<b>14.8</b>	14.4	14.4



Certificate L2367

**Laboratory** : WearCheck USA - 501 Madison Ave., Cary, NC 27513  
**Sample No.** : GFL0103224 **Received** : 11 Jan 2024  
**Lab Number** : 06057709 **Diagnosed** : 11 Jan 2024  
**Unique Number** : 10823658 **Diagnostician** : Wes Davis  
**Test Package** : FLEET

**GFL Environmental - 001 - Raleigh(CNG)**  
 3741 Conquest Drive  
 Garner, NC  
 US 27529  
 Contact: Craig Johnson  
 craig.johnson@gflenv.com  
 T: (919)662-7100  
 F: (919)662-7130

To discuss this sample report, contact Customer Service at 1-800-237-1369.  
 \* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.  
 Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)