

WEAR
CONTAMINATION
FLUID CONDITION


NORMAL NORMAL NORMAL

Heavy Equipment-Excavator 40t+/No Dealer Given 104009 KOMATSU PC400LC-7 A86691

Component Diesel Engine

CHEVRON DELO 400 XLE 15W40 (--- GAL)

CHEVRON DELO 400 XLE 13W40 (GAL)							
RECOMMENDATION	Test	UOM	Method	Limit/Abn	Current	History1	History2
Resample at the next service interval to monitor.	Sample Number		Client Info		LEC0039796		
	Sample Date		Client Info		04 Jan 2024		
	Machine Age	hrs	Client Info		7303		
	Oil Age	hrs	Client Info		0		
	Filter Age	hrs	Client Info		0		
	Oil Changed		Client Info		N/A		
	Filter Changed		Client Info		N/A		
	Sample Status				NORMAL		
WEAR	Iron	ppm	ASTM D5185m	>100	22		
All component wear rates are normal.	Chromium	ppm	ASTM D5185m	>20	<1		
	Nickel	ppm	ASTM D5185m		<1		
	Titanium	ppm	ASTM D5185m		0		
	Silver	ppm	ASTM D5185m	>3	0		
	Aluminum	ppm	ASTM D5185m		3		
	Lead	ppm	ASTM D5185m		0		
	Copper	ppm	ASTM D5185m		<1		
	Tin	ppm	ASTM D5185m		<1		
	Vanadium	ppm	ASTM D5185m		<1		
	White Metal	scalar	*Visual	NONE	NONE		
	Yellow Metal	scalar	*Visual	NONE	NONE		
CONTAMINATION	Silicon	ppm	ASTM D5185m		4		
There is no indication of any contamination in the oil.	Potassium	ppm	ASTM D5185m		0		
	Fuel		WC Method		<1.0		
	Water		WC Method	>0.2	NEG		
	Glycol		WC Method		NEG		
	Soot %	%	*ASTM D7844		0.2		
	Nitration	Abs/cm	*ASTM D7624	>20	7.0		
	Sulfation	Abs/.1mm	*ASTM D7415		21.9		
	Silt	scalar	*Visual	NONE	NONE		
	Debris	scalar	*Visual	NONE	NONE		
	Sand/Dirt	scalar	*Visual	NONE	NONE		
	Appearance Odor	scalar	*Visual *Visual	NORML	NORML		
				NORML	NORML		
<u></u>	Emulsified Water	scalar	*Visual	>0.2	NEG		
FLUID CONDITION	Sodium	ppm	ASTM D5185m		0		
	Boron	ppm	ASTM D5185m		367		
The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.	Barium	ppm	ASTM D5185m		0		
	Molybdenum	ppm	ASTM D5185m		87		
	Manganese	ppm	ASTM D5185m		<1		
	Magnesium	ppm	ASTM D5185m		425		
	Calcium	ppm	ASTM D5185m		1439		
	Phosphorus	ppm	ASTM D5185m		999		
	Zinc	ppm			1261		
	Sulfur	ppm	ASTM D5185m		3290		
	Oxidation	Abs/.1mm	*ASTM D7414		16.5		
	Base Number (BN)	0 0	ASTM D2896		7.7		
	Visc @ 100°C	cSt	ASTM D445	14.9	13.5		







Laboratory Sample No. Lab Number

Unique Number

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 : 06057910

: LEC0039796 : 10829292

11.5

Recieved Diagnosed

: 12 Jan 2024

Diagnostician : Don Baldridge Test Package : CONST (Additional Tests: TBN)

: 11 Jan 2024

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

MIDWEST MOLE 6814 W 350N GREENFIELD, IN US 46140 Contact: C.W. Kick

CKICK@MIDWESTMOLE.COM

T: (317)545-1335

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)