



ASCENDUM

OIL ANALYSIS REPORT

WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL



Machine Id
VOLVO L150H 6982
Component
Hydraulic System
Fluid
VOLVO SUPER HYDRAULIC OIL 46 (--- GAL)

RECOMMENDATION

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		ASC0006318	VCP413279	VCP421458
Sample Date		Client Info		03 Jan 2024	28 Aug 2023	03 May 2023
Machine Age	hrs	Client Info		3120	2853	1982
Oil Age	hrs	Client Info		3120	2853	1982
Filter Age	hrs	Client Info		0	0	0
Oil Changed		Client Info		N/A	Not Changd	Not Changd
Filter Changed		Client Info		N/A	Not Changd	Changed
Sample Status				NORMAL	NORMAL	NORMAL

WEAR

All component wear rates are normal.

Iron	ppm	ASTM D5185m	>50	10	4	3
Chromium	ppm	ASTM D5185m	>20	2	0	0
Nickel	ppm	ASTM D5185m	>10	0	<1	0
Titanium	ppm	ASTM D5185m		<1	0	<1
Silver	ppm	ASTM D5185m		0	0	0
Aluminum	ppm	ASTM D5185m	>20	2	0	3
Lead	ppm	ASTM D5185m	>20	1	<1	1
Copper	ppm	ASTM D5185m	>20	4	3	3
Tin	ppm	ASTM D5185m	>20	<1	0	0
Vanadium	ppm	ASTM D5185m		0	0	0
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE

CONTAMINATION










The system cleanliness is acceptable for your target ISO 4406 cleanliness code. The system and fluid cleanliness is acceptable.

Silicon	ppm	ASTM D5185m	>20	2	2	2
Potassium	ppm	ASTM D5185m	>20	2	2	0
Water		WC Method	>0.2	NEG	NEG	NEG
Particles >4µm		ASTM D7647	>5000	1909	2156	4699
Particles >6µm		ASTM D7647	>1300	598	327	1147
Particles >14µm		ASTM D7647	>160	54	11	111
Particles >21µm		ASTM D7647	>40	14	1	23
Particles >38µm		ASTM D7647	>10	1	0	2
Particles >71µm		ASTM D7647	>3	0	0	0
Oil Cleanliness		ISO 4406 (c)	>19/17/14	18/16/13	18/16/11	19/17/14
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG	NEG

FLUID CONDITION

The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.

Sodium	ppm	ASTM D5185m		0	2	<1
Boron	ppm	ASTM D5185m	14	0	4	0
Barium	ppm	ASTM D5185m	0.0	0	0	0
Molybdenum	ppm	ASTM D5185m	0.0	<1	0	0
Manganese	ppm	ASTM D5185m	0.0	<1	<1	<1
Magnesium	ppm	ASTM D5185m	2.6	<1	<1	<1
Calcium	ppm	ASTM D5185m	49	47	50	50
Phosphorus	ppm	ASTM D5185m	354	347	342	341
Zinc	ppm	ASTM D5185m	419	395	440	441
Sulfur	ppm	ASTM D5185m	3719	1928	1953	1602
Acid Number (AN)	mg KOH/g	ASTM D8045		0.31	0.33	0.28
Visc @ 40°C	cSt	ASTM D445	46	42.8	43.0	43.4



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : ASC0006318 **Received** : 11 Jan 2024
Lab Number : 06058011 **Diagnosed** : 12 Jan 2024
Unique Number : 10829393 **Diagnostician** : Wes Davis
Test Package : CONST

117 - ASCENDUM MACHINERY INC - GREENVILLE
 2002 N GREENE ST
 GREENVILLE, NC
 US 27834
 Contact: BRANDON JENKINS
 BRANDON.JENKINS@ASCENDUMMACHINERY.COM
 T:
 F: (704)494-8197

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)