


VOLVO A45G 353449


3 Axle


3 Axle Fluid GEAR OIL SAE 80W90 (GAL))						
RECOMMENDATION	Test	UOM	Method	Limit/Abn	Current	History1	History2
Resample at the next service interval to monitor. The fluid was not specified, however, a fluid match indicates that this fluid is (GENERIC) GEAR OIL SAE 80W90. Please confirm.	Sample Number		Client Info		ASC0006325		
	Sample Date		Client Info		04 Jan 2024		
	Machine Age	hrs	Client Info		1406		
	Oil Age	hrs	Client Info		1406		
	Filter Age	hrs	Client Info		0		
	Oil Changed		Client Info		N/A		
	Filter Changed		Client Info		N/A		
	Sample Status				NORMAL		
WEAR	Iron	ppm	ASTM D5185m	>900	241		
All component wear rates are normal.	Chromium	ppm	ASTM D5185m	>20	5		
	Nickel	ppm	ASTM D5185m		2		
	Titanium	ppm	ASTM D5185m		0		
	Silver	ppm	ASTM D5185m		0		
	Aluminum	ppm	ASTM D5185m	>30	<1		
	Lead	ppm	ASTM D5185m	>50	0		
	Copper	ppm	ASTM D5185m	>150	11		
	Tin	ppm	ASTM D5185m	>20	<1		
	Vanadium	ppm	ASTM D5185m		0		
	White Metal	scalar	*Visual	NONE	NONE		
	Yellow Metal	scalar	*Visual	NONE	NONE		
CONTAMINATION	Silicon	nnm	ASTM D5185m	>50	6		
There is no indication of any contamination in the oil.	Potassium	ppm	ASTM D5185m		2		
	Water	ppm	WC Method		NEG		
	Silt	scalar	*Visual	NONE	NONE		
	Debris	scalar	*Visual	NONE	NONE		
	Sand/Dirt	scalar	*Visual	NONE	NONE		
	Appearance	scalar	*Visual	NORML	NORML		
	Odor	scalar	*Visual	NORML	NORML		
	Emulsified Water	scalar	*Visual	>0.2	NEG		
FLUID CONDITION	Sodium	ppm	ASTM D5185m	>170	2		
The condition of the oil is acceptable for the time in service.	Boron	ppm	ASTM D5185m	400	119		
	Barium	ppm	ASTM D5185m	200	0		
	Molybdenum	ppm	ASTM D5185m	12	2		
	Manganese	ppm	ASTM D5185m		10		
	Magnesium	ppm	ASTM D5185m	12	2		
	Calcium	ppm	ASTM D5185m	150	258		
	Phosphorus	ppm	ASTM D5185m	1650	1923		
	Zinc	ppm	ASTM D5185m	125	141		
	Sulfur	ppm	ASTM D5185m	22500	21112		


Visc @ 40°C

ASTM D445 143











Certificate L2367

Laboratory Sample No.

Lab Number Unique Number : 10829824 Test Package : CONST

: ASC0006325 : 06058442

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 Recieved : 11 Jan 2024 Diagnosed : 12 Jan 2024

Diagnostician : Wes Davis

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation. Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

117 - ASCENDUM MACHINERY INC - GREENVILLE

2002 N GREENE ST GREENVILLE, NC US 27834

Contact: HUNTER DOLIVE

hunter.dolive@ascendummachinery.com

F: (704)494-8197