



OIL ANALYSIS REPORT

WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL

Area
Store 5 - Cross Lanes
Machine Id
JOHN DEERE TE-91
Component
Diesel Engine
Fluid
SHELL 15W40 (5 GAL)

RECOMMENDATION

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		LEC0041900	LECP181839	LEC0024181
Sample Date		Client Info		02 Jan 2024	02 Nov 2022	09 Mar 2022
Machine Age	hrs	Client Info		4916	3991	3562
Oil Age	hrs	Client Info		377	426	521
Filter Age	hrs	Client Info		377	426	521
Oil Changed		Client Info		Changed	Changed	Changed
Filter Changed		Client Info		Changed	Changed	Changed
Sample Status				NORMAL	ABNORMAL	ABNORMAL

WEAR

All component wear rates are normal.

Iron	ppm	ASTM D5185m	>51	20	▲ 56	▲ 67
Chromium	ppm	ASTM D5185m	>11	<1	<1	<1
Nickel	ppm	ASTM D5185m	>5	<1	2	2
Titanium	ppm	ASTM D5185m		<1	0	<1
Silver	ppm	ASTM D5185m	>3	0	0	<1
Aluminum	ppm	ASTM D5185m	>31	3	3	5
Lead	ppm	ASTM D5185m	>26	<1	<1	1
Copper	ppm	ASTM D5185m	>26	1	4	3
Tin	ppm	ASTM D5185m	>4	<1	<1	<1
Vanadium	ppm	ASTM D5185m		0	0	<1
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE

CONTAMINATION







There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185m	>120	7	6	8
Potassium	ppm	ASTM D5185m	>20	3	6	2
Fuel		WC Method	>2.1	<1.0	<1.0	<1.0
Water		WC Method	>0.21	NEG	NEG	NEG
Glycol		WC Method		NEG	NEG	NEG
Soot %	%	*ASTM D7844	>3	0.6	1.1	1
Nitration	Abs/cm	*ASTM D7624	>20	10.0	12.3	13.2
Sulfation	Abs/.1mm	*ASTM D7415	>30	24.5	28.1	29.4
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.21	NEG	NEG	NEG

FLUID CONDITION

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

Sodium	ppm	ASTM D5185m	>150	<1	4	4
Boron	ppm	ASTM D5185m		164	66	96
Barium	ppm	ASTM D5185m		0	0	0
Molybdenum	ppm	ASTM D5185m		206	31	243
Manganese	ppm	ASTM D5185m		<1	<1	1
Magnesium	ppm	ASTM D5185m		668	110	900
Calcium	ppm	ASTM D5185m		1350	2223	1713
Phosphorus	ppm	ASTM D5185m		851	937	929
Zinc	ppm	ASTM D5185m		983	1214	1056
Sulfur	ppm	ASTM D5185m		3085	3587	2700
Oxidation	Abs/.1mm	*ASTM D7414	>25	20.3	22.2	23.7
Base Number (BN)	mg KOH/g	ASTM D2896		7.4	7.5	9.1
Visc @ 100°C	cSt	ASTM D445		13.3	15.0	14.5



Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : LEC0041900 **Received** : 11 Jan 2024
Lab Number : 06058668 **Diagnosed** : 12 Jan 2024
Unique Number : 10830050 **Diagnostician** : Wes Davis
Test Package : CONST (Additional Tests: TBN)

C. J. HUGHES CONSTRUCTION
 PO BOX 7305
 HUNTINGTON, WV
 US 25776
 Contact: DEWEY SHEPPARD
 dsheppard@cjhughes.com
 T: (304)522-3868
 F: (304)743-5449

Certificate L2367
 To discuss this sample report, contact Customer Service at 1-800-237-1369.
 * - Denotes test methods that are outside of the ISO 17025 scope of accreditation.
 Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)