WEAR CONTAMINATION **FLUID CONDITION**

NORMAL NORMAL NORMAL

JOHN DEERE 325G 1T0325GKCMJ411159

Component Hydraulic System

Fluid

(not provided) /

RECOMMENDATION	Test	UOM	Method	Limit/Abn	Current	History1	History2
TEOOMMENDATION	Sample Number	00	Client Info		JR0158858		
Resample at the next service interval to monitor.	Sample Date		Client Info		10 Jan 2024		
	Machine Age	hrs	Client Info		805		
	Oil Age	hrs	Client Info		0		
	Filter Age	hrs	Client Info		0		
	Oil Changed	1110	Client Info		Not Changd		
	Filter Changed		Client Info		Not Change		
	Sample Status		Onone mile		NORMAL		
					·····		
WEAR All component wear rates are normal.	PQ		ASTM D8184		13		
	Iron	ppm	ASTM D5185m	>20	0		
	Chromium	ppm	ASTM D5185m	>10	<1		
	Nickel	ppm	ASTM D5185m	>10	0		
	Titanium	ppm	ASTM D5185m		<1		
	Silver	ppm	ASTM D5185m		0		
	Aluminum	ppm	ASTM D5185m	>10	2		
	Lead	ppm	ASTM D5185m		0		
	Copper	ppm	ASTM D5185m		<1		
	Tin	ppm	ASTM D5185m		<1		
	Vanadium	ppm	ASTM D5185m		0		
	White Metal	scalar	*Visual	NONE	NONE		
	Yellow Metal	scalar	*Visual	NONE	NONE		
CONTAMINATION	Silicon	ppm	ASTM D5185m	>20	0		
	Potassium	ppm	ASTM D5185m	>20	1		
The amount and size of particulates present in the system are acceptable. There is no indication of any contamination in the oil.	Water		WC Method	>0.1	NEG		
	Particles >4µm		ASTM D7647	>5000	389		
	Particles >6µm		ASTM D7647	>1300	92		
	Particles >14µm		ASTM D7647	>160	11		
	Particles >21µm		ASTM D7647	>40	3		
	Particles >38µm		ASTM D7647	>10	0		
	Particles >71µm		ASTM D7647	>3	0		
	Oil Cleanliness		ISO 4406 (c)	>19/17/14	16/14/11		
	Silt	scalar	*Visual	NONE	NONE		
	Debris	scalar	*Visual	NONE	NONE		
	Sand/Dirt	scalar	*Visual	NONE	NONE		
	Appearance	scalar	*Visual	NORML	NORML		
	Odor	scalar	*Visual	NORML	NORML		
	Emulsified Water	scalar	*Visual	>0.1	NEG		
FLUID CONDITION	Sodium	ppm	ASTM D5185m		0		
The Abilian is a constable for this field. The second of t	Boron	ppm	ASTM D5185m		0		
The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.	Barium	ppm	ASTM D5185m		0		
	Molybdenum	ppm	ASTM D5185m		<1		
	Manganese	ppm	ASTM D5185m		0		
	Magnesium	ppm	ASTM D5185m		<1		
	Calcium	ppm	ASTM D5185m		87		
	Phosphorus	ppm	ASTM D5185m		734		
	Zinc	ppm	ASTM D5185m		921		
	Sulfur	ppm	ASTM D5185m		1689		
	Acid Number (AN)	mg KOH/g	ASTM D8045		0.77		
	Visc @ 40°C	cSt	ASTM D445		62.7		





Certificate L2367

Laboratory Sample No. Lab Number **Unique Number**

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 : JR0158858 : 06058713

: 10830095

Recieved Diagnosed

Diagnostician : Don Baldridge Test Package : MOBCE (Additional Tests: PQ)

: 11 Jan 2024

: 14 Jan 2024

To discuss this sample report, contact Customer Service at 1-800-237-1369.

Contact: MIKE JENKINS MIKE.JENKINS@JAMESRIVEREQUIPMENT.COM

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation. Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012) T: (540)292-3494 F: (540)337-1495

98 EXPO ROAD

US 22939

JRE - FISHERSVILLE

FISHERSVILLE, VA