



WEAR	<b>NORMAL</b>
CONTAMINATION	<b>NORMAL</b>
FLUID CONDITION	<b>NORMAL</b>

Area  
**A.A. BIRCH**  
Machine Id  
**[A.A. BIRCH] 006 616455-6**  
Component  
**Starboard Reduction Gear**  
Fluid  
**CHEVRON MEROPA 320 (230 GAL)**

**RECOMMENDATION**

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		<b>MW0053877</b>	MW0060285	MW0060276
Sample Date		Client Info		<b>01 Jan 2024</b>	01 Nov 2023	31 Aug 2023
Machine Age	hrs	Client Info		<b>85384</b>	83431	82795
Oil Age	hrs	Client Info		<b>39851</b>	38298	33262
Filter Age	hrs	Client Info		<b>0</b>	0	0
Oil Changed		Client Info		<b>Not Changd</b>	Changed	Not Changd
Filter Changed		Client Info		<b>None</b>	None	None
Sample Status				<b>NORMAL</b>	NORMAL	NORMAL

**WEAR**

All component wear rates are normal.

Iron	ppm	ASTM D5185m	>150	<b>25</b>	19	23
Chromium	ppm	ASTM D5185m	>10	<b>&lt;1</b>	0	0
Nickel	ppm	ASTM D5185m	>10	<b>&lt;1</b>	<1	<1
Titanium	ppm	ASTM D5185m		<b>&lt;1</b>	<1	<1
Silver	ppm	ASTM D5185m		<b>0</b>	0	0
Aluminum	ppm	ASTM D5185m	>25	<b>3</b>	4	3
Lead	ppm	ASTM D5185m	>100	<b>0</b>	0	0
Copper	ppm	ASTM D5185m	>50	<b>7</b>	4	6
Tin	ppm	ASTM D5185m	>10	<b>0</b>	0	0
Vanadium	ppm	ASTM D5185m		<b>0</b>	0	0
White Metal	scalar	*Visual	NONE	<b>NONE</b>	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	<b>NONE</b>	NONE	NONE

**CONTAMINATION**







There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185m	>50	<b>2</b>	1	2
Potassium	ppm	ASTM D5185m	>20	<b>2</b>	0	1
Water		WC Method	>0.1	<b>NEG</b>	NEG	NEG
Silt	scalar	*Visual	NONE	<b>NONE</b>	NONE	NONE
Debris	scalar	*Visual	NONE	<b>NONE</b>	LIGHT	NONE
Sand/Dirt	scalar	*Visual	NONE	<b>NONE</b>	NONE	NONE
Appearance	scalar	*Visual	NORML	<b>NORML</b>	NORML	NORML
Odor	scalar	*Visual	NORML	<b>NORML</b>	NORML	NORML
Emulsified Water	scalar	*Visual	>0.1	<b>NEG</b>	NEG	NEG

**FLUID CONDITION**

The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.

Sodium	ppm	ASTM D5185m		<b>1</b>	2	4
Boron	ppm	ASTM D5185m	20	<b>4</b>	4	3
Barium	ppm	ASTM D5185m		<b>0</b>	0	2
Molybdenum	ppm	ASTM D5185m	0	<b>2</b>	<1	2
Manganese	ppm	ASTM D5185m		<b>&lt;1</b>	<1	<1
Magnesium	ppm	ASTM D5185m		<b>6</b>	5	6
Calcium	ppm	ASTM D5185m	25	<b>85</b>	78	81
Phosphorus	ppm	ASTM D5185m	235	<b>300</b>	260	253
Zinc	ppm	ASTM D5185m		<b>18</b>	25	37
Sulfur	ppm	ASTM D5185m		<b>9163</b>	7899	9169
Acid Number (AN)	mg KOH/g	ASTM D8045	0.56	<b>0.70</b>	0.65	0.75
Visc @ 40°C	cSt	ASTM D445	304	<b>334</b>	334	331



Certificate L2367

**Laboratory** : WearCheck USA - 501 Madison Ave., Cary, NC 27513  
**Sample No.** : MW0053877 **Received** : 11 Jan 2024  
**Lab Number** : 06058813 **Diagnosed** : 12 Jan 2024  
**Unique Number** : 10830195 **Diagnostician** : Wes Davis  
**Test Package** : MAR 2

To discuss this sample report, contact Customer Service at 1-800-237-1369.

\* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

**INGRAM BARGE**  
 900 S 3RD ST  
 PADUCAH, KY  
 US 42003

Contact: DALE MORIE  
 dale.morie@ingrambarga.com  
 T: (270)415-4467  
 F: (615)695-3697