
WEAR CONTAMINATION FLUID CONDITION **ABNORMAL ABNORMAL NORMAL**

JOHN DEERE 3035D 1PY3035DEKB000888

Component Hydrostatic

JOHN DEERE HY-GARD HYD/TRANS (--- GAL)

| RECOMMENDATION | Test | UOM | Method | Limit/Abn | Current | History1 | History2 |
|--|------------------|----------|--------------|-----------|-------------------|----------|----------|
| | Sample Number | | Client Info | | JR0137484 | | |
| No corrective action is recommended at this time. Resample at the next service interval to monitor. | Sample Date | | Client Info | | 09 Jan 2024 | | |
| | Machine Age | hrs | Client Info | | 669 | | |
| | Oil Age | hrs | Client Info | | 669 | | |
| | Filter Age | hrs | Client Info | | 669 | | |
| | Oil Changed | | Client Info | | Not Changd | | |
| | Filter Changed | | Client Info | | Not Changd | | |
| | Sample Status | | | | ABNORMAL | | |
| VEAR | PQ | | ASTM D8184 | | 36 | | |
| TEAT . | Iron | ppm | ASTM D5185m | >31 | 42 | | |
| The iron level is abnormal. | Chromium | ppm | ASTM D5185m | | <1 | | |
| | Nickel | ppm | ASTM D5185m | >5 | 1 | | |
| | Titanium | ppm | ASTM D5185m | | <1 | | |
| | Silver | ppm | ASTM D5185m | | 0 | | |
| | Aluminum | ppm | ASTM D5185m | >10 | 2 | | |
| | Lead | ppm | ASTM D5185m | >11 | <1 | | |
| | Copper | ppm | ASTM D5185m | >41 | 11 | | |
| | Tin | ppm | ASTM D5185m | >5 | <1 | | |
| | Vanadium | ppm | ASTM D5185m | | 0 | | |
| | White Metal | scalar | *Visual | NONE | NONE | | |
| | Yellow Metal | scalar | *Visual | NONE | NONE | | |
| CONTAMINATION | Silicon | ppm | ASTM D5185m | >31 | 7 | | |
| ONTAMINATION | Potassium | ppm | ASTM D5185m | | 8 | | |
| There is a high amount of silt (particulates < 14 microns in size) present in the oil. | Water | ppiii | WC Method | >0.1 | NEG | | |
| | Particles >4µm | | ASTM D7647 | | <u> </u> | | |
| | Particles >6µm | | ASTM D7647 | | <u> 19015</u> | | |
| | Particles >14µm | | ASTM D7647 | >640 | 40 | | |
| | Particles >21µm | | ASTM D7647 | >160 | 7 | | |
| | Particles >38μm | | ASTM D7647 | >40 | 0 | | |
| | Particles >71μm | | ASTM D7647 | >10 | 0 | | |
| | Oil Cleanliness | | ISO 4406 (c) | >21/19/16 | <u>^</u> 25/21/12 | | |
| | Silt | scalar | *Visual | NONE | NONE | | |
| | Debris | scalar | *Visual | NONE | NONE | | |
| | Sand/Dirt | scalar | *Visual | NONE | NONE | | |
| | Appearance | scalar | *Visual | NORML | NORML | | |
| | Odor | scalar | *Visual | NORML | NORML | | |
| | Emulsified Water | scalar | *Visual | >0.1 | NEG | | |
| LUID CONDITION | Sodium | ppm | ASTM D5185m | >21 | 9 | | |
| EOID OONDITION | Boron | ppm | ASTM D5185m | | 137 | | |
| The AN level is acceptable for this fluid. The condition of the oils additive package is suitable for further service. | Barium | ppm | ASTM D5185m | | 6 | | |
| | Molybdenum | ppm | ASTM D5185m | | <1 | | |
| | Manganese | ppm | ASTM D5185m | | 2 | | |
| | Magnesium | ppm | ASTM D5185m | 145 | 12 | | |
| | Calcium | ppm | ASTM D5185m | | 3726 | | |
| | Phosphorus | ppm | ASTM D5185m | 1290 | 1192 | | |
| | Zinc | ppm | ASTM D5185m | 1640 | 1476 | | |
| | Sulfur | ppm | ASTM D5185m | | 11983 | | |
| | Acid Number (AN) | mg KOH/g | ASTM D8045 | 1.8 | 1.45 | | |
| | Visc @ 40°C | cSt | ASTM D445 | 57.0 | 83.7 | | |





Certificate L2367

Laboratory Sample No. Lab Number **Unique Number**

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 : JR0137484 : 06058881

: 10830263

: 11 Jan 2024 Recieved Diagnosed : 16 Jan 2024 Diagnostician : Jonathan Hester

Test Package : MOBCE (Additional Tests: PQ, PRTCOUNT) To discuss this sample report, contact Customer Service at 1-800-237-1369. * - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

JRE - WILKESBORO 288 WESTGATE DRIVE WILKESBORO, NC US 28697

Contact: BUTCH JANES bjanes@jamesriverequipment.com

T: (336)973-8201 F: (336)973-8496 Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)